



PRODUCT PROFILE

GENERIC DESCRIPTION Advanced Thermoset Solution Fluoropolymer

COMMON USAGE A low VOC, fluoropolymer coating that provides an ultra-durable finish with user friendly brush, roll and conventional spray application. It has outstanding color and gloss retention even in the most severe exposures. Under certain conditions, it may be used to restore aged fluoropolymer coil applied coatings or for OEM applications. Contact Tnemec Technical Services or your local Tnemec representative for details.

COLORS Refer to Tnemec Color Guide. **Note:** Certain colors may require multiple coats depending on method of application and finish coat color. The preceding coat should be in the same color family, but noticeably different. Upon selection of the finish coat color, the intermediate coat color may be selected by Tnemec Company.

FINISH Semi-Gloss

PERFORMANCE CRITERIA Contact your Tnemec representative for specific test results.

COATING SYSTEM

PRIMERS Series 1, 27, 27WB, 66, L69, L69F, N69, N69F, V69, V69F, 90-75, 90-97, H90-97, 91-H₂O, 94-H₂O, 115, 118, 135, 161, 394, 1224. **Note:** Series 1 and 394 require an intermediate coat prior to topcoating with Series 1071V. **Note:** Series 118 is typically used to overcoat, sound, existing coating systems. See product data sheet for more information.

INTERMEDIATE Series 73, 750, 1075, 1075U, 1095 (Intermediate coat may be required for some applications, please contact your Tnemec coating consultant.)

Note: When topcoating with Series 1071V, the following maximum recoat times apply: Over 27, 66, L69, L69F, N69, N69F, V69, V69F, 135, 161, 14 days; over itself and 90-75, 30 days; over 750, 1075, 1075U, 1095, 45 days; over 1, 394, 60 days; over 27WB, 73, 90-97, H90-97, 91-H₂O, 94-H₂O, 1224, 90 days.

SURFACE PREPARATION

EXTERIOR EXPOSURE See primer product data sheet for surface preparation recommendation.

ALL SURFACES Must be clean, dry and free of oil, grease and other contaminants.

TECHNICAL DATA

VOLUME SOLIDS 61.0 ± 2.0% (mixed) †

RECOMMENDED DFT 2.0 to 3.0 mils (50 to 75 microns) per coat. **Note:** Number of coats and thickness requirements will vary with substrate, application method and exposure. Contact your Tnemec representative.

CURING TIME

Temperature	To Touch	To Handle	Minimum Recoat ‡
90°F (32°C)	30 minutes	4-6 hours	6-8 hours
70°F (21°C)	30 minutes	6-8 hours	10-12 hours
50°F (10°C)	1 hour	12-15 hours	16-24 hours

‡ Maximum recoat: 30 days. Curing time varies with surface temperature, air movement, humidity and film thickness. **Note:** For faster curing and low-temperature applications, add No. 44-710 Urethane Accelerator; see separate product data sheet.

VOLATILE ORGANIC COMPOUNDS

Unthinned: 1.05 lbs/gallon (125 grams/litre)
Unthinned: 0.51 lbs/gallon (61 grams/litre) (TBAC Exempt)
Thinned 10% (No. 65 Thinner): 1.05 lbs/gallon (125 grams/litre)
Thinned 10% (No. 65 Thinner): 0.51 lbs/gallon (61 grams/litre) (TBAC Exempt)
Thinned 10% (No. 63 Thinner): 1.71 lbs/gallon (205 grams/litre)
Thinned 10% (No. 63 Thinner): 1.29 lbs/gallon (154 grams/litre) (TBAC Exempt) †

HAPS

Unthinned: 0.01 lbs/gal solids
Thinned 10% (No. 65 Thinner): 0.01 lbs/gal solids
Thinned 10% (No. 63 Thinner): 0.07 lbs/gal solids †

THEORETICAL COVERAGE

878 mil sq ft/gal (24.0 m²/L at 25 microns) †

NUMBER OF COMPONENTS

Two: Part A and Part B

MIXING RATIO

By volume: Eight (Part A) to one (Part B)

PACKAGING

	PART A (partially filled)	PART B (partially filled)	Yield (mixed)
Medium Kit	5 gallon pail	1/2 gallon can	3 gallons (11.35L)
Small Kit	1 gallon can	1 pint can	1 gallon (3.79L)

NET WEIGHT PER GALLON

13.31 ± 0.25 lbs (6.03 ± .11 kg) (mixed) †

STORAGE TEMPERATURE

Minimum 20°F (-7°C) Maximum 110°F (43°C)

TEMPERATURE RESISTANCE

(Dry) Continuous 250°F (121°C) Intermittent 275°F (135°C)

SHELF LIFE

12 months at recommended storage temperature

FLASH POINT - SETA

Part A: 86°F (28°C) Part B: >200°F (93°C)

HEALTH & SAFETY

Paint products contain chemical ingredients which are considered hazardous. Read container label warning and Material Safety Data Sheet for important health and safety information prior to the use of this product.
Keep out of the reach of children.

FLUORONAR® | SERIES 1071V

APPLICATION

COVERAGE RATES

	Dry Mils (Microns)	Wet Mils (Microns)	Sq Ft/Gal (m ² /Gal)
Suggested	2.5 (65)	4.0 (101)	385 (35.8)
Minimum	2.0 (50)	3.5 (90)	481 (44.7)
Maximum	3.0 (75)	5.0 (127)	321 (29.8)

Allow for overspray and surface irregularities. Film thickness is rounded to the nearest 0.5 mil or 5 microns. Application of coating below minimum or above maximum recommended dry film thicknesses may adversely affect coating performance. †

MIXING

Stir contents of the container marked Part A, making sure no pigment remains on the bottom. Add the contents of the can marked Part B to Part A while under agitation. Continue agitation until the two components are thoroughly mixed. Do not use mixed material beyond pot life limits. **Caution: Part B is moisture-sensitive and will react with atmospheric moisture. Keep unused material tightly closed at all times.**

THINNING

Thinning is required for proper application. For brush, roller, and air spray, thin up to 10% (82 mL) per gallon with No. 63 Thinner. **Note:** In areas that require lower VOC, use No. 65 Thinner. **Caution: Do not add thinner if more than thirty (30) minutes have elapsed after mixing.**

POT LIFE

2 hours at 50°F (10°C) 2 hours at 70°F (21°C) 1 hour at 90°F (32°C)

APPLICATION EQUIPMENT

Air Spray

Gun	Fluid Tip	Air Cap	Air Hose ID	Mat'l Hose ID	Atomizing Pressure	Pot Pressure
DeVilbiss JGA	E	765 or 704	5/16" or 3/8" (7.9 or 9.5 mm)	3/8" or 1/2" (9.5 or 12.7 mm)	70-90 psi (4.9-6.2 bar)	10-20 psi (0.7-1.4 bar)

Low temperatures or longer hoses require higher pot pressure.

Use appropriate tip/atomizing pressure for equipment, applicator technique and weather conditions.

Roller: Use 1/4" (6.4 mm) synthetic woven nap cover. Do not use medium or long nap roller covers.

Brush: Recommended for small areas only. Use high quality natural or synthetic bristle brushes.

SURFACE TEMPERATURE

Minimum 40°F (4°C) Maximum 120°F (49°C)

The surface should be dry and at least 5°F (3°C) above the dew point.

Cure time necessary to resist direct contact with moisture at surface temperature:

Temperature	To Resist Moisture
100°F (38°C)	2 hours
90°F (32°C)	3 1/2 hours
80°F (27°C)	5 hours
70°F (21°C)	7 hours
60°F (16°C)	11 hours
50°F (10°C)	21 1/2 hours
40°F (4°C)	44 hours

If the coating is exposed to moisture before the preceding cure parameters are met, dull, flat or spotty-appearing areas may develop. Actual times will vary with air movement, film thickness and humidity.

CLEANUP

Flush and clean all equipment immediately after use with the recommended thinner or MEK.

† Values may vary with color.

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.