



# METALLIC CLEARCOAT

# 1079-0762

## PRODUCT PROFILE

<b>GENERIC DESCRIPTION</b>	Aliphatic Acrylic Polyurethane
<b>COMMON USAGE</b>	A unique clear coat used to both enhance the finish and extend the long-term weathering qualities of metallic pigmented coatings. Resists most graffiti markings. Where VOC regulations apply, this product can only be sold or used as part of a faux finishing coating system.
<b>COLORS</b>	Clear
<b>FINISH</b>	Semi-Gloss
<b>PERFORMANCE CRITERIA</b>	Extensive test data available. Contact your Tnemec representative for specific test results.

## COATING SYSTEM

**BASE COATS** Series 1077, 1078. **Note:** Series 1079-0762 Metallic Clearcoat should be applied within 24 hours of a previous Series 1079-0762 or Series 1078 application and within 21 days of a 1077 application.

## SURFACE PREPARATION

**ALL SURFACES** Prepare by method suitable for exposure and service. (See Primer Product Data Sheet for surface preparation recommendations.)  
Must be clean, dry and free of oil, grease and other contaminants.

## TECHNICAL DATA

**VOLUME SOLIDS** 57% ± 2.0% (mixed)  
**RECOMMENDED DFT** 1.0 to 2.0 mils (25 to 50 microns) per coat.  
**CURING TIME**

Temperature	To Touch	To Handle	Minimum To Recoat	Maximum To Recoat†
75°F (24°C)	1-2 hours	7-8 hours	8 hours	24 hours

To resist moisture condensation: 6 hours.  
Curing time varies with surface temperature, air movement, humidity and film thickness.  
† If exceeded, scarify before applying an additional coat.

## VOLATILE ORGANIC COMPOUNDS

**Unthinned:** 2.00 lbs/gallon (240 grams/litre)  
**Thinned 5% (No. 49 Thinner):** 2.00 lbs/gallon (240 grams/litre)  
**Thinned 5% (No. 2 Thinner):** 2.31 lbs/gallon (277 grams/litre)  
**Thinned 10% (No. 2 Thinner):** 2.59 lbs/gallon (310 grams/litre)

**THEORETICAL COVERAGE** 914 mil sq ft/gal (22.4 m<sup>2</sup>/L at 25 microns). See APPLICATION for coverage rates.

**NUMBER OF COMPONENTS** Three: Part A, Part B and Part C

**MIXING RATIO** By volume: Four (Part A) to One (Part B) Part C: See note under Mixing.

**PACKAGING** Small Kit: Consists of a one-gallon can of Part A, a quart can of Part B, an 8 oz bottle of Part C. When mixed yields 1.31 gallons.

**NET WEIGHT PER GALLON** 8.77 ± 0.25 lbs (3.99 kg ± 0.11) (mixed)

**STORAGE TEMPERATURE** Minimum 20°F (-7°C) Maximum 110°F (43°C)

**TEMPERATURE RESISTANCE** (Dry) Continuous 250°F (121°C) Intermittent 275°F (135°C)

**SHELF LIFE** Parts A, B & C: 12 months at recommended storage temperature.

**FLASH POINT - SETA** Part A: 64°F (18°C) Part B: 78°F (25°C) Part C: 88°F (31°C)

**HEALTH & SAFETY** Paint products contain chemical ingredients which are considered hazardous. Read container label warning and Material Safety Data Sheet for important health and safety information prior to the use of this product.  
**Keep out of the reach of children.**

# METALLIC CLEARCOAT | 1079-0762

**APPLICATION**

**COVERAGE RATES**

	Dry Mills (Microns)	Wet Mills (Microns)	Sq Ft/Kit (m <sup>2</sup> /Gal) Small Kit
Suggested	1.5 (40)	2.5 (65)	798 (74)
Minimum	1.0 (25)	1.5 (40)	1197 (111)
Maximum	2.0 (50)	3.0 (75)	598 (55)

Allow for overspray and surface irregularities. Film thickness is rounded to the nearest 0.5 mil or 5 microns. Application of coating below minimum or above maximum recommended dry film thicknesses may adversely affect coating performance.

**MIXING**

**Note:** Add Part C Accelerator according to the following chart.

Surface Temp. Range	Amount of Part C to Add (Small Kit - Parts A and B mixed)
40°F to 70°F (4°C to 21°C)	Full amount supplied (8 oz or 235 mL)
70°F to 80°F (21°C to 27°C)	50% of amount supplied (4 oz or 120 mL)
Above 80°F (27°C)	25% of amount supplied (2 oz or 60 mL)

Pour Part A into a clean container large enough to hold all three components. Add Part C Accelerator to Part A while under agitation. Mix thoroughly. Add Part B to the mixture of Parts A, C while under agitation. Continue agitation until all components are thoroughly mixed. **Important:** Mixing ratio is four (Part A) to one (Part B) by volume.

**THINNING**

Use No. 49 or No. 2 Thinner. For air spray, thin up to 10% per gallon. For roller, thin up to 5% per gallon. **Caution: Do not add thinner if more than thirty (30) minutes have elapsed after mixing.**

**POT LIFE**

1 hour at 77°F (25°C) 30 minutes at 100°F (38°C)

**Note:** See chart at beginning of Mixing instructions.

**APPLICATION EQUIPMENT**

**Air Spray**

Gun	Fluid Tip	Air Cap	Air Hose ID	Mat'l Hose ID	Atomizing Pressure	Pot Pressure
DeVilbiss MBC or JGA	E	765 or 704	5/16" or 3/8" (7.9 or 9.5 mm)	3/8" or 1/2" (9.5 or 12.7 mm)	70-90 psi (4.8-6.2 bar)	10-20 psi (0.7-1.4 bar)

Low temperature or longer hoses require higher pot pressure. Proper atomization is necessary to obtain a smooth finish.

**Airless Spray:** Not recommended.

**Roller:** Use 1/4" (6.4 mm) synthetic woven nap cover. Do not use medium or long nap roller covers.

**Brush:** Recommended for small areas only. Use high quality natural or synthetic bristle brushes.

**SURFACE TEMPERATURE**

Minimum 40°F (4°C) Maximum 120°F (49°C)

The surface should be dry and at least 5°F (3°C) above the dew point.

**CLEANUP**

Flush and clean all equipment immediately after use with the recommended thinner or xylol.

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.