



PRODUCT PROFILE

GENERIC DESCRIPTION Elevated Temperature Epoxy Vinyl Ester

COMMON USAGE Series 1422 is an FDA-compliant, trowel-grade, high temperature lining suitable for tanks and vessels in food grade service environments or where high temperature conditions are required. Highly filled with glass-flake, it is specially formulated for exceptional service in thermal cycling and chemical reaction vessels. Replaces ProPolymer 4865T.

COLORS 901 White, 908 Lavender, 909 Dent Yellow

FINISH Semi-gloss

SPECIAL QUALIFICATIONS Complies with the requirements and extractive limitations of US FDA 21 CFR Part 175.300 Resinous and Polymeric Coatings for tanks or other repeated use direct food storage or mixing vessels 5 gallons or greater under conditions of use C-E with all food types. Compliance was based upon raw material supplier documents, and third party analytical and extractive test results (HKGH02404141).

COATING SYSTEM

PRIMERS **Steel:** Self-priming or 1402
Concrete: Series 1402

SURFACE PREPARATION

STEEL **Immersion Service:** SSPC-SP10/NACE 2 Near-White Metal Blast Cleaning or ISO Sa 2 1/2 Very Thorough Blast Cleaning with a minimum angular anchor profile of 3.0 mils. **Note:** For aggressive cargo exposures or immersion in elevated temperatures, an SSPC-SP5/NACE 1 or ISO Sa 3 Blast Cleaning to Visually Clean Steel with a minimum angular anchor profile of 3.0 mils may be required. Contact Tnemec Technical Service for more information.

CONCRETE Allow new cast-in-place concrete to cure a minimum of 28 days at 75°F (24°C). Verify concrete dryness in accordance with ASTM F 1869 "Standard Test Method for Measuring Moisture Vapor Emission Rate of Concrete Subfloor Using Anhydrous Calcium Chloride" (moisture vapor transmission should not exceed three pounds per 1,000 square feet in a 24 hour period), F 2170 "Standard Test Method for Determining Relative Humidity in Concrete using in situ Probes" (relative humidity should not exceed 80%), or D 4263 "Standard Test Method for Indicating Moisture in Concrete by the Plastic Sheet Method" (no moisture present). Prepare concrete surfaces in accordance with NACE No. 6/SSPC-SP13 Joint Surface Preparation Standards and ICRI Technical Guidelines. Abrasive blast, shot-blast, water jet or mechanically abrade concrete surfaces to remove laitance, curing compounds, hardeners, sealers and other contaminants and to provide a minimum ICRI-CSP 3 surface profile. Large cracks, voids and other surface imperfections should be filled with a recommended filler or surfacer.

ALL SURFACES Must be clean, dry and free of oil, grease and other contaminants.

TECHNICAL DATA

VOLUME SOLIDS 85% (mixed). Series 1422 contains a reactive monomer and some loss will occur during application and cure. Actual solids by volume will vary depending upon temperature and air movement.

RECOMMENDED DFT 30.0 to 60.0 mils (762 to 1524 microns) per coat.

CURING TIME

Temperature	To Recoat	Immersion Service
90°F (32°C)	3 hours min. 3 days max.	20 hours
75°F (24°C)	4 hours min. 4 days max.	24 hours

VOLATILE ORGANIC COMPOUNDS

EPA Method 24
0.41 lbs/gallon (49 grams/litre)

THEORETICAL COVERAGE

1,363 mil sq ft/gal (33.4 m²/L at 25 microns). See APPLICATION for coverage rates.

NUMBER OF COMPONENTS

Two: Part A (base) and Part B (catalyst)

PACKAGING

	Part A (Partially Filled)	Part B (Partially filled)	Yield (mixed)
Medium Kit	6 gallon pail	Pint bottle	5.0 gallons (18.9 L)
Small Kit	3 gallon can	4 oz bottle	1.0 gallons (3.7 L)

NET WEIGHT PER GALLON

11.5 lbs ± 0.25 lbs (5.2 ± 0.11 kg) (mixed)

STORAGE TEMPERATURE

Minimum 50°F (10°C) Maximum 75°F (24°C)

TEMPERATURE RESISTANCE

(Dry) Continuous 240°F (115°C)

SHELF LIFE

Part A: 3 months; Part B: 12 months at recommended storage temperatures.
DUE TO THE REACTIVE NATURE OF THE VINYL ESTER RESINS AND THE CORRESPONDING LIMITED SHELF LIFE, EXPEDITIOUS USE OF THIS PRODUCT IS SUGGESTED, SINCE JOBSITE STORAGE CONDITIONS ARE BEYOND TNEMEC'S CONTROL, THIS PRODUCT IS NON-RETURNABLE.

FLASH POINT - SETA

Part A: 79°F (26°C) Part B: 133°F (56°C)

HEALTH & SAFETY

Paint products contain chemical ingredients which are considered hazardous. Read container label warning and Safety Data Sheet for important health and safety information prior to the use of this product.
Keep out of the reach of children.

PROPOLYMER™ | SERIES 1422

APPLICATION

COVERAGE RATES

	Dry Mils (Microns)	Wet Mils (Microns)	Sq Ft/Gal (m²/Gal)
Minimum	30.0 (762)	35.0 (896)	45 (4)
Maximum	60.0 (1524)	71.0 (1792)	23 (2)

Actual spreading rates will vary with surface profile, amount of overspray and surface irregularities. Application of coating below minimum or above maximum recommended dry film thicknesses may adversely affect coating performance. THIS PRODUCT SHOULD NOT BE APPLIED BELOW 60°F (16°C) MATERIAL TEMPERATURE.

MIXING

Power mix contents of Part A (base) thoroughly, making sure no pigment remains on the bottom of the can. Add the Part B (catalyst) slowly to the Part A while under agitation. Ensure that all Part B is blended with Part A by scraping the pail walls with a flexible spatula. Continue to agitate until thoroughly mixed. Care should be exercised so as not to entrap air in the mixed material. **Note:** Do not over mix, caution should be taken to avoid shearing the glass flake. Do not use mixed material beyond pot life limits.

THINNING

Do not thin.

POT LIFE

45 minutes at 75°F (24°C)

Note: At higher temperatures pot life will decrease (use caution in spray equipment).

APPLICATION EQUIPMENT

Troweled: Use a high grade metal trowel with rounded corners in addition to if needed, a mortar hawk to assist in transfer of mixed materials.

Finish Roll: Use a high quality 1/4" nap, shed resistant, woven fabric roller, lightly dampened with Series 44-809 Smoothing Agent over the surface while Series 1422 is still in a semi-fluid condition.

SURFACE TEMPERATURE

Minimum 60°F (16°C), optimum 70°F (21°C), maximum 100°F (38°C). The surface should be dry and at least 5°F (3°C) above the dew point. At surface temperatures below 60°F (16°C), Series 1422 will not cure properly or obtain maximum chemical resistance. At relative humidities above 75%, the cure of this coating may be retarded. It is also recommended that all precautions be taken to insure that adequate forced-air ventilation exists.

MATERIAL TEMPERATURE

For optimum application, handling and performance, the material temperature during application should be between 60°F and 90°F (16°C and 32°C). Temperature will affect the workability. Cool temperatures increase viscosity and lengthen pot life. Warm temperatures will decrease viscosity and shorten pot life.

CLEANUP

Clean equipment immediately after use with MEK.

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.