



# TNEME-TAPE SERIES 152

## PRODUCT PROFILE

**GENERIC DESCRIPTION** Polyester Fabric  
**COMMON USAGE** Flexible tape provides reinforcement for coatings that will bridge cracks and expansion joints.

## COATING SYSTEM

**TOPCOATS** Series 156, 157, 158, 159

## TECHNICAL DATA

PACKAGING	PRODUCT	PACKAGING	DIMENSION
	152-205 Tneme-Tape HD	rolls	3" x 164' (7.6 x 50 m)

NET WEIGHT	PRODUCT	WEIGHT PER ROLL
	152-205 Tneme-Tape HD	9.0 oz (255 g)

**STORAGE TEMPERATURE** Minimum 30°F (-1°C) Maximum 110°F (43°C)  
**SHELF LIFE** 5 years when stored inside at recommended storage temperature.

## APPLICATION

**APPLICATION** Repair cracks, gaps, expansion joints, etc., wider than 0.125" with heavy duty 152-205 HD Tneme-Tape.

1. Prime, if required, according to topcoat product data sheet.
2. Apply one coat of either 156 or 158 over the area of the crack, joint, etc., to achieve half the total coverage given in the topcoat application instructions: Ensure that the coating is brushed or sprayed over the entire repair area to be reinforced and sufficiently to either side to allow the 152 Tneme-Tape to be completely embedded.
3. Press 152 Tneme-Tape into the coating with a brush, to remove all air pockets.
4. Brush the membrane which comes through the tape over the surface and allow to dry, thereby leaving the reinforcing fabric encapsulated in the coating.
5. The entire area to be coated can then be coated per the topcoat product data sheet.

**Note:** Apply even coats to avoid build-up of thick patches within the tape. Allow thorough drying between each stage. Joints should be butted together and not overlapped. The tape itself should be applied in its natural relaxed condition, do not stretch 152 during application.

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.

