



FIBERGLASS MAT 211-226 & -227

PRODUCT PROFILE

GENERIC DESCRIPTION	1.5-ounce chopped strand Fiberglass Mat
COMMON USAGE	Provides fiberglass mat reinforcement to epoxy & vinyl ester lining systems. Increases impact, thermal shock and abrasion resistance for greater durability.
SIZE	Series 211-226: 6 in x 268 ft (134 sq ft) or Series 211-227: 38 in x 268 ft (848 sq ft)

COATING SYSTEM

BASE COATS	Series 206SC, 215, 237SC, 239SC, 252SC, 1415, 1416, 1418
SATURANT	Series 206SC, 237SC, 239SC, 252SC, 1415, 1416, 1418
TOPCOATS	Series 206SC, 237SC, 239SC, 252SC, 1415 (pigmented), 1416 (pigmented), 1418 (pigmented), 1430, 1432, 1436

TECHNICAL DATA

PACKAGING	Available in full rolls: Series 211-226: 6 in x 268 ft or Series 211-227: 38 in x 268 ft
STORAGE TEMPERATURE	Minimum 40°F (4°C) Maximum 80°F (27°C)
SHelf LIFE	Indefinite, when stored in unopened bags at 70°F (21°C) with less than 50% relative humidity.
HEALTH & SAFETY	Read container label warning and Safety Data Sheet for important health and safety information prior to the use of this product. Keep out of reach of children

APPLICATION

APPLICATION	Measure the length desired (equal to the area to be base coated.) This area will vary with application rate. Cut the glass with scissors or fiberglass shears. Roll up the cut piece of mat tightly for easier handling. While the base coat is still wet, lay and press the 1.5 oz chopped strand reinforcing mat into the surface (free fiber side of mat into base coat, shiny bonded side facing out). Using a rib roller, backroll the bonded side of the mat to fully embed and remove any air pockets. Once mat is placed, immediately saturate until mat is completely wet out. Caution: The saturant coat should be applied at a thickness to only wet out the fiberglass mat. Any attempt to build a film on top of the mat may result in sags and runs.
APPLICATION EQUIPMENT	1/8" Rib Roller

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.

Tnemec Company, Inc. 6800 Corporate Drive Kansas City, Missouri 64120-1372 +1 816-483-3400 www.tnemec.com