



# ABRASION RESISTANT POWDER

## SERIES 211-9215

### PRODUCT PROFILE

<b>GENERIC DESCRIPTION</b>	Specially Blended Abrasion Resistant Ultra-Fine Bulking Powder
<b>COMMON USAGE</b>	Series 211-9215 is used to create a highly abrasion resistant mortar for areas of high wear and impingement. Series 211-9215 is added to Series 1415, 1416 or 1418 and applied over glass roving or directly to properly prepared and primed surfaces.
<b>COLORS</b>	Series 211-9215: Brown Series 211-9214: Off White (Silica-Free)

### TECHNICAL DATA

<b>PACKAGING</b>	Available in 50-pound bags.
<b>STORAGE TEMPERATURE</b>	Minimum 40°F (4°C) Maximum 80°F (27°C) <b>Note:</b> Material should be stored in a dry conditioned space.
<b>HEALTH &amp; SAFETY</b>	This product contains chemical ingredients which are considered hazardous. Read container label warning and Material Safety Data Sheet for important health and safety information prior to the use of this product. <b>Keep out of the reach of children.</b>

### APPLICATION

<b>MIXING</b>	Use an appropriate type of mortar mixer and slowly blend recommended amounts of bulking powder with properly proportioned and mixed Part A and B mixed liquids. <b>Note:</b> Bulking additives are normally added at a rate of 20 pounds per mixed gallon of liquids but may be adjusted as needed for certain applications. Adjustments are usually no more than 5-pounds, plus or minus, the recommended 20 pounds. <b>Note:</b> Reference the Series 1415, 1416 or 1418 product data sheets for additional information.
---------------	--

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.

Tnemec Company, Inc. 6800 Corporate Drive Kansas City, Missouri 64120-1372 +1 816-483-3400 [www.tnemec.com](http://www.tnemec.com)