



EXCELLATHANE SERIES 256

PRODUCT PROFILE

GENERIC DESCRIPTION	Modified Aliphatic Polyaspartic
COMMON USAGE	An extremely fast-curing, multi-purpose and finish coat resin with low temperature cure capability. Used to build aggregate, colored quartz or decorative flake filled floor topping systems. It can also be used as a clear or pigmented finish coat over systems built using Series 256 or systems built using epoxy, or polyurethane modified concrete floor toppings that have been fully broadcast with aggregate, colored quartz or colored flake. Series 256 will provide protection against impact, abrasion and mild chemicals, has excellent gloss and color retention, and resistance to yellowing. This low VOC, 100% solids urethane exhibits low odor characteristics allowing for use near occupied spaces.
COLORS	Supplied as a clear coat, may be field tinted with available Series 821 color pack in the 16 standard StrataShield colors and limited custom colors. Color packs are sold separately. Contact Tnemec for availability. Note: Certain colors may require multiple coats depending on the method of application and finish coat color.
FINISH	Gloss. The texture of the finished surface will depend on the film thickness and number of coats applied. Note: Application as a clear topcoat may lead to a cloudy appearance if the product is overworked, applied too thick, or applied too far into its pot life. This product has a short working time. Caution should be taken to apply the material immediately after mixing and to not overwork the product when rolling.
SPECIAL QUALIFICATIONS	Series 256 was tested in accordance with, and passed, the California Department of Public Health CDPH/EHLB/Standard Method Version 1.1, 2010 emissions testing and meets qualifications of LEED v4, Collaborative for High Performance Schools, and Living Building Challenge.

COATING SYSTEM

SURFACER/FILLER/PATCHER	Series 215, or Series 201, 256 or 257 mixed with select aggregate fillers may be used for small patches or crack repairs. Certain high-early strength, cementitious repair mortars are also acceptable for deeper filling and patching. For more extensive repairs and additional information, contact your Tnemec representative or Tnemec Technical Services.
PRIMERS	Self-priming or Series 241, 242, 245. Note: When applying over standard epoxies or epoxy primers the epoxy is typically fully broadcast with aggregate, colored quartz or colored flake or mechanically abraded using 60 grit sandpaper or coarser. Note: When building systems using 222, 224, 233, 237, 238, 241, 242 and 245 refer to applicable product data sheet for appropriate primer/intermediate selection.
INTERMEDIATE	Series 222, 224, 233, 237, 238, 241, 245, 256, 257. Note: If Series 222, 224, 233, 237, 238, 241 or 245 is used as an intermediate coat, aggregate, colored quartz, or decorative flake is typically broadcast to refusal into the intermediate coat prior to topcoating with 256.
TOPCOATS	Series 247, 248, 256, 257. Note: Before applying Series 247/248 over coatings with a smooth, glossy surface, thoroughly scarify the Series 256 using a power sander and 100 grit sandpaper, No. 60 mesh sanding screen or a coarse stripping pad to eliminate surface tension. Failing to uniformly degloss the entire surface or thoroughly clean all surface contamination may lead to fisheyes and/or poor adhesion. Sanding or scarification is not required when topcoating textured coatings (i.e. aggregate or colored quartz broadcast to refusal) with Series 247/248 if maximum recoat time of the previous coating is met.

SURFACE PREPARATION

CONCRETE	<p>Allow new poured-in-place concrete to cure a minimum of 28 days at 75°F (24°C). Verify concrete dryness in accordance with ASTM F 1869 "Standard Test Method for Measuring Moisture Vapor Emission Rate of Concrete Subfloor Using Anhydrous Calcium Chloride" (moisture vapor transmission should not exceed three pounds per 1,000 square feet in a 24 hour period), F 2170 "Standard Test Method for Determining Relative Humidity in Concrete using in situ Probes" (relative humidity should not exceed 80%), or D 4263 "Standard Test Method for Indicating Moisture in Concrete by the Plastic Sheet Method" (no moisture present). Note: The testing listed above cannot guarantee avoidance of future moisture related problems particularly with existing concrete slabs. This is especially true if the use of an under slab moisture vapor barrier cannot be confirmed or concrete contamination from oils, chemical spills, unreacted silicates, chlorides or Alkali Silica Reaction (ASR) is suspected.</p> <p>Prepare concrete surfaces in accordance with NACE No. 6/SSPC-SP13 Joint Surface Preparation Standards and ICRI Technical Guidelines. Abrasive blast, shot-blast, water jet or mechanically abrade concrete surfaces to remove laitance, curing compounds, hardeners, sealers and other contaminants and to provide a minimum ICRI-CSP 3 or greater surface profile. Large cracks, voids and other surface imperfections should be filled with a recommended filler or surfacer. Note: For moisture content exceeding 3 lbs per 1,000 sq ft or relative humidity in excess of 80%, Series 241 may be substituted for the primer. Refer to the Series 241 product data sheet for more information.</p>
ALL SURFACES	Must be clean, dry and free of oil, grease and other contaminants.

TECHNICAL DATA

VOLUME SOLIDS	100% (mixed)
RECOMMENDED DFT	Primer: 6.0 to 12.0 mils (150-305 microns) per coat. Broadcast: 1/16" to 1/8" (Double broadcast or slurry broadcast required to achieve 1/8") Grout coat: 8.0 to 16.0 mils (203 to 406 microns) Intermediate or Topcoat: 8.0 to 16.0 mils (203 to 406 microns) Note: Do not exceed 20 mils (500 microns) dry film thickness.

EXCELLATHANE | SERIES 256

CURING TIME

Temperature	To Topcoat	Light Traffic	Place in Service
75°F (24°C) & 50% R.H.	2 to 3 hours minimum, 48 hours maximum*	3 to 5 hours*	6 to 12 hours*

*For applications at 75°F and 50% relative humidity, if more than 48 hours has elapsed between coats of Series 256, the surface must be mechanically abraded before recoating. For applications between 70% and 80% relative humidity, if more than 36 hours has elapsed between coats of Series 256, the surface must be mechanically abraded before recoating. Curing time varies with surface temperature, air movement, humidity and film thickness. Relative humidity greatly impacts the working time, cure speed and recoat window of Series 256. Working time and the recoat time will decrease and cure rates increase when applying in higher humidity conditions. **Do not apply if relative humidity is greater than 80%.**

VOLATILE ORGANIC COMPOUNDS

Parts A & B:
Unthinned: 0.09 lbs/gallon (11 grams/litre)
Thinned 5%: 0.47 lbs/gallon (56 grams/litre)

HAPS

0.0 lbs/gal solids

THEORETICAL COVERAGE

1,604 mil sq ft/gal (39.4 m²/L at 25 microns). See APPLICATION for coverage rates.

NUMBER OF COMPONENTS

Liquids—Two: Part A and Part B (2 parts A to 1 part B by volume)
 Optional Field Colorant: Series 821 is sold separately and available in pint containers in 16 standard StrataShield colors and limited custom colors.

PACKAGING

	PART A	PART B	Yield (mixed)
Large Kit	2-5 gallon pails	1-5 gallon pail	15 gallons
Small Kit	2-1 gallon cans	1-1 gallon can	3 gallons

Optional Field Colorant: Series 821 field applied colorants are sold separately and available in pint containers in 16 standard StrataShield colors and limited custom colors. Order two pints per small kit or ten pints per large kit. Pint containers are filled with 12 ounces of colorant (eight ounces of colorant should be calculated per mixed gallon of clear Series 256, thus 24 ounces per 3 gallon small kit and 120 ounces per 15 gallon large kit).

Decorative Flake Application: Decorative flake may be purchased through Tnemec as Series 224 Part C or purchased separately from a supplier providing equivalent type flake.

Aggregate & Decorative Quartz Broadcast Application: Purchase clean, dry, (30/50 mesh) silica sand or approved equal. The aggregate is calculated at one-half pound per sq ft (2.4 kg/m²) per broadcast application or one pound per sq ft (4.8 kg/m²) for a double broadcast. Additional aggregate is required to accommodate for waste or loss during application or to make coving material.

NET WEIGHT PER GALLON

9.06 ± 0.25 lbs (mixed)

STORAGE TEMPERATURE

Minimum 50°F (10°C) Maximum 90°F (32°C)
 Material should be stored at temperatures between 70°F and 90°F (21°C and 32°C) for at least 48 hours prior to use.

TEMPERATURE RESISTANCE

(Dry) Continuous 250°F (121°C) Intermittent 275°F (135°C)

SHelf LIFE

12 months at recommended storage temperature.

FLASH POINT - SETA

N/A

HEALTH & SAFETY

This product contains chemical ingredients which are considered hazardous. Read container label warning and Material Safety Data Sheet for important health and safety information prior to the use of this product.
Keep out of the reach of children.

APPLICATION

COVERAGE RATES

Primer: 6.0-12.0 dry mils (150-305 microns), 6.0-12.0 wet mils (150-305 microns), 134-267 sq ft/gal (12.2-24.3 m²)
Decorative Flake Application: Spread the mixed liquids (Parts A and B) at a rate of 160 sq ft (3.94 m²L) per gallon or approximately 10-12 mils (255-305 microns) wet. **Broadcast Randomly:** This technique provides a "speckled" appearance and allows the primer color to show through. Broadcast evenly across the floor at around one lb per 100 sq ft without completely covering the underlying primer. **Broadcast to Refusal:** Apply the flake at a rate of four to five sq ft per lb until no liquids are showing on the surface.
Aggregate & Decorative Quartz Broadcast Application: Spread the mixed liquids (Parts A and B) at a rate of 80-100 sq ft (7.4-9.3 m²) per gallon or approximately 15-20 mils (380-510 microns) wet. Broadcast the aggregate into the liquid within five to ten minutes until a uniformly dry appearance is obtained. After the first broadcast layer cures, forming a thickness approximately 1/16" (1.6mm) thick, remove the excess aggregate and apply a second application to obtain a minimum thickness of 1/8" (3.2mm).
Grout coat: 8.0-16.0 dry mils (203 to 406 microns), 8.0-16.0 dry mils (203 to 406 microns) wet mils, 100-201 sq ft/gal (9.3-18.6 m²).
Intermediate or Topcoat: 8.0-16.0 dry mils (203 to 406 microns), 8.0-16.0 dry mils (203 to 406 microns) wet mils, 100-201 sq ft/gal (9.3-18.6 m²). The texture of the finished surface will depend on the film thickness and number of coats applied. **Note:** Application as a clear topcoat may lead to a cloudy appearance if the product is overworked, applied too thick, or applied too far into its pot life. This product has a short working time. Caution should be taken to apply the material immediately after mixing and to not overwork the product when rolling.

WORKING TIME

16 to 18 minutes at 75°F (24°C) & 50% R.H.
 Warmer temperatures and high humidity will decrease pot life, working time and recoat time and increase cure time.

MIXING

Use a variable speed drill with a PS Jiffy blade. Slowly mix 2 parts A component, and while under agitation add 1 part B component and mix for a minimum of two minutes. Ensure that all Part B is blended with Part A by scraping the pail walls with a flexible spatula. **Note:** Material will set up quickly and must be applied immediately. Installation difficulty can occur when applying Excellathane in highly humid conditions. Excellathane's working time is inversely related to the relative humidity; in high humidity environments, the product's working time is reduced because of the excessive moisture in the atmosphere. Limiting moisture interaction with the material will hinder the cure rate. To increase the working time, once Part A and B are completely mixed, pour only a portion onto the substrate and leave the remainder in the mixing bucket until ready to be used. This will prevent moisture in the air from coming into contact with mixed material. However, pouring the entire mixture directly onto the floor can accelerate the cure and decrease open time. Do not mix several kits at once; mix only one kit at a time. Do not add freshly mixed material to previously mixed material.
Caution: Do not reseat mixed material. An explosion hazard may be created.

THINNING

Thin up to 5% with Tnemec No. 72 Thinner as needed. **Caution:** Do not exceed 5% thinning.

APPLICATION EQUIPMENT

Squeegee or trowel and backroll. Brush small areas only.

EXCELLATHANE | SERIES 256

SURFACE TEMPERATURE	Minimum of 40°F (4°C), optimum 50°F to 75°F (10°C to 24°C), maximum of 80°F (27°C). The substrate temperature should be at least 5°F (3°C) above the dew point.
MATERIAL TEMPERATURE	For optimum application, handling and performance, the material temperature during application should be between 60°F and 75°F (16°C and 24°C). Temperature and humidity will affect the workability. Cool temperatures increase viscosity and decrease workability. Warm temperatures and high humidity will decrease pot life and working time and increase cure speed.
AMBIENT HUMIDITY	Humidity must be below 80%. Application of the coating above the maximum recommended dry film thickness or at relative humidities above 80% may cause bubbles to form in the cured film.
CLEANUP	Flush and clean all equipment immediately after use with xylene or MEK.

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.

Tnemec Company, Inc. 6800 Corporate Drive Kansas City, Missouri 64120-1372 +1 816-483-3400 www.tnemec.com