

## PRODUCT PROFILE

<b>GENERIC DESCRIPTION</b>	Aliphatic Polyester Polyurethane
<b>COMMON USAGE</b>	Extremely hard, chemical-resistant clear urethane floor coating used as a finish coat for a variety of floor coating systems. It has superb flow characteristics, excellent resistance to abrasion, wet conditions, corrosive fumes and chemical contact. Gloss among the best of air dried finishes. Typically used over epoxy and urethane flooring systems for increased abrasion and chemical resistance. Contains a blend of ultraviolet (UV) light absorbers for enhanced gloss retention and resistance to UV degradation.
<b>COLORS</b>	Clear
<b>FINISH</b>	Gloss

## COATING SYSTEM

<b>PRIMERS</b>	<b>Horizontal Concrete:</b> Series 201, 203, 205, 280, 281, 287
<b>INTERMEDIATE</b>	Series 205, 210, 222, 223, 224, 237, 238, 280, 281, 284, 285, 287, 290 and 291. <b>Note:</b> Scarification using a power sander and 100 grit sandpaper, No. 60 mesh sanding screen or a coarse stripping pad is required if topcoating Series 295 with itself. <b>Note:</b> When applying Series 295 over a broadcast or mortar system, an epoxy grout coat is required. <b>Note:</b> Because epoxies will chalk and discolor when exposed to ultraviolet light, exterior exposures require a pigmented urethane over epoxy coatings before the Series 295 may be applied.

## SURFACE PREPARATION

<b>ALL SURFACES</b>	Must be clean, dry and free of oil, grease and other contaminants. Existing coatings require scarification and compatibility testing.
---------------------	---

## TECHNICAL DATA

<b>VOLUME SOLIDS</b>	62 ± 2.0% (mixed)
<b>RECOMMENDED DFT</b>	2.0 to 3.0 mils (50 to 75 microns) per coat.
<b>CURING TIME</b>	

Temperature	Min Recoat	To Service	Chemical Resistance
75°F (24°C)	12 hours	24 hours	7 days

Curing time varies with surface temperature, air movement, humidity and film thickness.

<b>VOLATILE ORGANIC COMPOUNDS</b>	<b>Unthinned:</b> 2.86 lbs/gallon (343 grams/litre) <b>Thinned 8%:</b> 3.12 lbs/gallon (373 grams/litre)
-----------------------------------	---

<b>HAPS</b>	<b>Unthinned:</b> 0.47 lbs/gal solids <b>Thinned 8%:</b> 0.46 lbs/gal solids
-------------	---

**THEORETICAL COVERAGE** 994 mil sq ft/gal (24.4 m<sup>2</sup>/L at 25 microns). See APPLICATION for coverage rates. †

**NUMBER OF COMPONENTS** Two: Part A and Part B (2.5 Parts A to 1 Part B by volume)

	PART A (Partially filled)	PART B (Partially filled)	When Mixed Yield
Large Kit	3 gallon pail	1 gallon can	3 gallons (11.4L)
Small Kit	1 gallon can	1/2 gallon can	1 gallon (3.79L)

**NET WEIGHT PER GALLON** 8.78 ± 0.25 lbs (3.98 ± .11 kg) (mixed)

**STORAGE TEMPERATURE** Minimum 20°F (-7°C) Maximum 110°F (43°C)

**TEMPERATURE RESISTANCE** (Dry) Continuous 250°F (121°C) Intermittent 275°F (135°C)

**SHELF LIFE** 12 months at recommended storage temperature.

**FLASH POINT - SETA** Part A: 108°F (41°C) Part B: >200°F (93°C)

**HEALTH & SAFETY** Paint products contain chemical ingredients which are considered hazardous. Read container label warning and Material Safety Data Sheet for important health and safety information prior to the use of this product.  
**Keep out of the reach of children.**

# CLEAR CRU | SERIES 295

## APPLICATION

### COVERAGE RATES

	Dry Mils (Microns)	Wet Mils (Microns)	Sq Ft/Gal (m <sup>2</sup> /Gal)
Suggested	2.5 (65)	4.0 (100)	398 (37.0)
Minimum	2.0 (50)	3.0 (75)	497 (46.2)
Maximum	3.0 (75)	5.0 (125)	331 (30.8)

Allow for overspray and surface irregularities. Film thickness is rounded to the nearest 0.5 mil or 5 microns. Application of coating below minimum or above maximum recommended dry film thicknesses may adversely affect coating performance. †

### MIXING

Stir contents of each container, until uniform in consistency. Slowly mix 2.5 parts A component to 1 part B while under agitation. Continue agitation until the two components are thoroughly mixed. Do not use mixed material beyond pot life limits. Part B is moisture-sensitive and will react with atmospheric moisture. Unused material must be kept tightly closed at all times. *Important: Mixing ratio is 2.5 (Part A) to 1 (Part B) by volume.*

### THINNING

Thin up to 8% or 10 ounces (190 mL) per gallon with No. 39 Thinner. **Note:** Thinning is required for proper application. **Caution: Do not add thinner if more than thirty (30) minutes have elapsed after mixing.**

### POT LIFE

1 1/2 hours at 60°F (16°C)    1 1/4 hours at 77°F (25°C)    1 hour at 100°F (38°C)

### APPLICATION EQUIPMENT

**Spray:** Not recommended.

**Roller:** Use a 1/4" (6.4 mm) high quality and shed-resistant synthetic nap cover. Do not use medium or long nap roller covers.

**Brush:** Use high quality natural or synthetic bristle brushes.

### SURFACE TEMPERATURE

Minimum 40°F (4°C)    Maximum 135°F (57°C)

The surface should be dry and at least 5°F (3°C) above the dew point. This product is moisture-sensitive until cured.

Application of the coating above the maximum recommended dry film thickness may cause bubbles to form in the cured film.

### CLEANUP

Flush and clean all equipment immediately after use with the recommended thinner or MEK.

† Values vary with application.

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.