



ELASTO-SHIELD® SERIES 406

PRODUCT PROFILE

- GENERIC DESCRIPTION** Aromatic Polyurethane Hybrid
- COMMON USAGE** A two-component, fast setting, monolithic coating designed to provide a durable polyurethane lining in a single-coat, multi-pass spray application applied with plural component equipment. This high performance coating has excellent chemical, thermal shock and abrasion resistance. It is ideal for application to steel or concrete in water and wastewater treatment, secondary containment and for tank linings and bottoms. Recommended for immersion service. **Note:** All orders are subject to approval based upon project scope, applicator qualification and appropriate equipment configuration.
- COLORS** WH06 Off-White. Other colors may be available with minimum size orders, contact your Tnemec representative. **Note:** Colors will change when exposed to sunlight.
- SPECIAL QUALIFICATIONS** Series 406-WH06 Off-White is certified by **NSF International** in accordance with **NSF/ANSI Std.61**. Series 406-WH06 is qualified for use on the interior of potable water storage tanks and reservoirs of 50,000 gallons capacity or greater and pipes 36 inches in diameter or greater. **WH06 Off-White is the only color that is NSF certified in Series 406.** Series 1, 91-H₂O, 94-H₂O, N140, N140F, V140 and V140F are the only Std. 61 certified primers for use with Series 406. Reference the "Search Listings" section of the NSF website at www.nsf.org for details on the maximum allowable DFT. Conforms to **AWWA C 222**. Conforms to **AWWA D 102 Inside Coating System No. 4**. Contact your Tnemec representative for systems and additional information.
- PERFORMANCE CRITERIA** Contact your Tnemec representative for specific test results.

COATING SYSTEM

- SURFACER/FILLER/PATCHER** Series 215, 218. **Note:** For more extensive repairs and additional information, contact your Tnemec representative or Tnemec Technical Service.
- PRIMERS** **Concrete & CMU:** Series N140, N140F, V140, V140F, 201.
Steel: Self-priming or Series 1, 90-97, 91-H₂O, 94-H₂O, N140, N140F, V140, V140F.
When topcoating with Series 406, the following recoat times apply:

	90-97/91-H ₂ O/94-H ₂ O (Min/Max)	201 (Min/Max)	140 (Min/Max)	140F (Min/Max)	1 (Min/Max)
At 90°F (32°C)	4 hrs/14 days	4 hrs/3 days	7 hrs/7 days	4 hrs/7 days	4 hrs/30 days
At 75°F (24°C)	4 hrs/30 days	6 hrs/5 days	10 hrs/14 days	6 hrs/14 days	4 hrs/30 days
At 55°F (13°C)	4 hrs/30 days	8 hrs/7 days	24 hrs/30 days	24 hrs/30 days	4 hrs/30 days
At 35°F (2°C)	4 hrs/30 days	N/A	N/A	24 hrs/30 days	4 hrs/30 days

- TOPCOATS** Series 290, 297, 1080, 1081. **Note:** Not for use in immersion service. **Note:** When topcoating with Series 290, 297, 1080 or 1081, recoat time for Series 406 is 24 hours minimum/5 days maximum.

SURFACE PREPARATION

- STEEL** Refer to the appropriate primer data sheet for specific recommendations.
Non-Immersion Service: SSPC-SP6/NACE 3 Commercial Blast Cleaning.
Immersion Service: SSPC-SP10/NACE 2 Near-White Blast Cleaning.
Note: When self-priming on steel, a minimum angular anchor profile of 3.0 mils is required. For all other applications, refer to the primer data sheet for recommendations.
- CONCRETE** Allow new cast-in-place concrete to cure a minimum of 28 days at 75°F (24°C). Verify concrete dryness and prepare concrete surfaces in accordance with NACE No. 6/SSPC-SP13 Joint Surface Preparation Standards and ICRI Technical Guidelines. Moisture vapor transmission should not exceed three lbs per 1,000 sq ft in a 24 hour period (Reference ASTM F 1869 "Standard Test Method for Measuring Moisture Vapor Emission Rate of Concrete Subfloor Using Anhydrous Calcium Chloride"). Relative humidity should not exceed 80% (Reference ASTM F 2170 "Standard Test Method for Determining Relative Humidity in Concrete using in situ Probes"). No moisture present when using a "plastic sheet test" (Reference ASTM D 4263 "Standard Test Method for Indicating Moisture in Concrete by the Plastic Sheet Method"). Abrasive blast, waterjet or mechanically abrade concrete surfaces to remove laitance, curing compounds, hardeners, sealers and other contaminants and to provide a minimum ICRI-CSP 5 or greater surface profile. Large cracks, voids and other surface imperfections should be filled with a recommended filler or surfacer.
- CMU** Allow new mortar to cure 28 days. Surfaces must be clean, dry, sound and free of all contaminants. Level all protrusions and mortar spatter. CMU must be filled with Series 218 or 215.
- ALL SURFACES** Must be clean, dry and free of oil, grease and other contaminants.

ELASTO-SHIELD® | SERIES 406

TECHNICAL DATA

VOLUME SOLIDS 100% (mixed) †
RECOMMENDED DFT 25.0 to 125.0 mils (635 to 3175 microns). Maximum of 75 mils DFT for applications in potable water.
CURING TIME

	To Recoat (Maximum)	Return to Service WH06 (NSF/ANSI Std. 61)	Return to Service Non-Potable
At 95°F (35°C)	24 hours	72 hours	36 hours
At 75°F (24°C)	24 hours	72 hours	36 hours
At 35°F (2°C)	24 hours	7 days	7 days

Note: There is a seven day return to service time for potable water immersion if N140, N140F, V140 or V140F is used as a primer. This does not apply if Series 406 is applied direct or another approved primer is used.

Note: If the maximum recoat window has been exceeded, the Series 406 coated surface must be mechanically abraded and wiped with MEK prior to topcoating. Curing time varies with surface temperature, air movement, humidity and film thickness. **Ventilation:** When used in enclosed areas, provide adequate ventilation during application and cure.

VOLATILE ORGANIC COMPOUNDS EPA Method 24: 0 lbs/gallon (0 grams/litre) †
HAPS 0 lbs/gal solids
THEORETICAL COVERAGE 1,600 mil sq ft/gal (39.3 m²/L at 25 microns) †
NUMBER OF COMPONENTS Two: Part A (iso) and Part B (resin)
MIXING RATIO One (Part A) to Two (Part B) by volume
PACKAGING 55 gallon (208.2 L) drums (with 50 gallon fill) and 5 gallon (18.9 L) pails. (Order in multiples of 3)
NET WEIGHT PER GALLON Part A: 10.26 ± 0.20 lbs. Part B: 9.51 ± 0.20 lbs. †
STORAGE TEMPERATURE Minimum 50°F (10°C) Maximum 90°F (32°C)
TEMPERATURE RESISTANCE (Dry) Continuous 250°F (121°C) Intermittent 300°F (149°C)
SHELF LIFE 12 months at recommended storage temperature.
FLASH POINT - SETA Part A: >350°F (177°C) Part B: >350°F (177°C)
HEALTH & SAFETY This product contains chemical ingredients which are considered hazardous. Read container label warning and Material Safety Data Sheet for important health and safety information prior to the use of this product.
Keep out of the reach of children.

APPLICATION

COVERAGE RATES	Dry Mils (Microns)	Wet Mils (Microns)	Sq Ft/Gal (m ² /Gal)
Minimum	25.0 (635)	25.0 (635)	64 (6.0)
Maximum	125.0 (3175)	125.0 (3175)	13 (1.2)

Allow for overspray and surface irregularities. Application of coating below minimum suggested film thickness may adversely affect coating performance. Reference the "Search Listings" section of the NSF website at www.nsf.org for details on the maximum allowable DFT.

MIXING DO NOT AGITATE PART A. Agitate Part B making sure no pigment remains on the bottom of the can. **DO NOT MIX PART A WITH PART B.** Use a 1 (Iso): 2 (Resin) ratio plural component heated airless spray unit. **Note:** Part A must be heated to 90°F to 100°F (32°C to 38°C) prior to and during the application and the Part B heated to 110°F to 120°F (43°C to 49°C) prior to and during application. Prior to use: Keep containers tightly sealed. Components will react with moisture. For Parts A & B, attach desiccant filter through bung hole to remove moisture from air entering the drum. Cap partial drums with nitrogen gas to prevent moisture contamination.

THINNING **DO NOT THIN.** Thinning will adversely affect performance properties and negate **NSF/ANSI Std. 61 Certification** for potable water contact applications.

APPLICATION EQUIPMENT **HEATED PLURAL COMPONENT AIRLESS EQUIPMENT ONLY.**
Contact Tnemec Technical Service for equipment recommendations.
Brush: Recommended for small areas, repairs and weld seams.

SURFACE TEMPERATURE Minimum 20°F (-7°C) Maximum 120°F (49°C)
 The surface should be dry and at least 5°F (3°C) above the dew point. **Note:** Dehumidification is required if humidity is above 85%. **Note:** To reduce the effects of outgassing when applied to concrete/CMU, the surface temperature should be stable or descending and out of direct sunlight.

CLEANUP Flush and clean all equipment immediately after use with Tnemec No. 2 or No. 42 Thinner, MEK or xylene. Use Tnemec No. 74 Thinner when needed to comply with VOC regulations.

† Values may vary with color.

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.