



CHROME ALUMINUM SERIES 43-36

PRODUCT PROFILE

GENERIC DESCRIPTION Alkyd Aluminum

COMMON USAGE Metallic aluminum finish for protection against weather, heat and mild industrial fumes. Used on primed or previously-painted carbon and galvanized steel: tank exteriors, piping, equipment and structures. Not for use on surfaces that are continually wet or sweat frequently.

COLORS Aluminum

FINISH Low sheen

COATING SYSTEM

PRIMERS **Steel:** Series 37H
Galvanized Steel and Non-Ferrous Metal: Series 27. **Note:** Apply an intermediate coat of Series 27 or scarify the surface of Series 27 that has been exterior exposed for 3 weeks or longer prior to topcoating with 43-36. Brush blasting with fine abrasive is the preferred method of scarification. Consult the latest version of Tnemec Technical Bulletin 10-78 or contact your Tnemec representative or Tnemec Technical Services for more information.

SURFACE PREPARATION

ALL SURFACES Must be clean, dry and free of oil, grease and other contaminants. Remove rust and paint not tightly bonded. Spot prime.

TECHNICAL DATA

VOLUME SOLIDS 37.0 ± 2.0%

RECOMMENDED DFT 1.0 to 2.0 mils (25 to 50 microns) per coat. **Note:** Number of coats required will vary depending on exposure conditions and other variables. Contact your Tnemec representative.

CURING TIME

Temperature	To Touch	To Handle	To Recoat
75°F (24°C)	2 hours	16 hours	24 hours

Curing time varies with surface temperature, air movement, humidity and film thickness.

VOLATILE ORGANIC COMPOUNDS

4.1 lbs/gallon (487 grams/litre)

HAPS

0.03 lbs/gal solids

THEORETICAL COVERAGE

593 mil sq ft/gal (14.55 m²/L at 25 microns). See APPLICATION for coverage rates.

NUMBER OF COMPONENTS

One

PACKAGING

55 gallon (208.2L) drums, 5 gallon (18.9L) pails and 1 gallon (3.79L) cans.

NET WEIGHT PER GALLON

7.80 ± 0.25 lbs (3.54 ± .11 kg)

STORAGE TEMPERATURE

Minimum 20°F (-7°C) Maximum 110°F (43°C)

TEMPERATURE RESISTANCE

(Dry) Continuous 400°F (204°C) Intermittent 450°F (232°C)

SHELF LIFE

24 months at recommended storage temperature.

FLASH POINT - SETA

110°F (43°C)

HEALTH & SAFETY

Paint products contain chemical ingredients which are considered hazardous. Read container label warning and Safety Data Sheet for important health and safety information prior to the use of this product.
Keep out of the reach of children.

APPLICATION

COVERAGE RATES

	Dry Mils (Microns)	Wet Mils (Microns)	Sq Ft/Gal (m ² /Gal)
Suggested	1.0 (25)	3.0 (75)	593 (55.1)
Minimum	1.0 (25)	3.0 (75)	593 (55.1)
Maximum	2.0 (50)	5.5 (140)	297 (27.6)

Allow for overspray and surface irregularities. Film thickness is rounded to the nearest 0.5 mil or 5 microns. Application of coating below minimum or above maximum recommended dry film thicknesses may adversely affect coating performance.

MIXING

Stir thoroughly, making sure no pigment remains on the bottom of the can.

THINNING

Do not thin.

CHROME ALUMINUM | SERIES 43-36

APPLICATION EQUIPMENT

Air Spray

Gun	Fluid Tip	Air Cap	Air Hose ID	Mat'l Hose ID	Atomizing Pressure	Pot Pressure
DeVilbiss MBC or JGA	E	765 or 704	5/16" or 3/8" (7.9 or 9.5 mm)	3/8" or 1/2" (9.5 or 12.7 mm)	60-80 psi (4.2-5.5 bar)	10-20 psi (0.7-1.4 bar)

Low temperatures or longer hoses require higher pot pressure.

Airless Spray

Tip Orifice	Atomizing Pressure	Mat'l Hose ID	Manifold Filter
0.013"-0.017" (330-430 microns)	1800-3000 psi (124-207 bar)	1/4" or 3/8" (6.4 or 9.5 mm)	60 mesh (250 microns)

Use appropriate tip/atomizing pressure for equipment, applicator technique and weather conditions.

Roller: Use 1/4" or 3/8" (6.4 mm or 9.5 mm) high quality synthetic woven nap covers.

Brush: Use high quality natural or synthetic bristle brushes.

SURFACE TEMPERATURE

Minimum 40°F (4°C) Maximum 120°F (49°C)

The surface should be dry and at least 5°F (3°C) above the dew point.

CLEANUP

Flush and clean all equipment immediately after use with the recommended thinner or mineral spirits.

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.