



EPOXY ACCELERATOR SERIES 44-700

PRODUCT PROFILE

GENERIC DESCRIPTION	Modified Amine
COMMON USAGE	Special additive for use with select epoxies to accelerate the cure rate and allow for coating application at temperatures down to 35°F (2°C).
COLORS	Clear Amber
SPECIAL QUALIFICATIONS	Series 44-700 Epoxy Accelerator is considered by NSF International as an NSF /ANSI Std. 61 certified component of Series L140, N140, V140 and 1220 when used in potable water applications.
CAUTION	Adding Series 44-700 Accelerator to Series L69, N69, L140, N140 and V140 will: <ol style="list-style-type: none"> 1. Increase gloss 10 or more units on 60 degree meter. 2. Slightly decrease acid resistance. 3. Produce slightly yellower white and pastel colors. 4. Substantially change some clean yellow, green, orange and red colors.

TECHNICAL DATA

VOLUME SOLIDS 100%
CURING TIME

With: Series L69, N69, L140, N140 or V140

Temperature	To Touch	To Handle	To Recoat	Immersion
75°F (24°C)	2 hours	4 hours	5 hours	7 days
65°F (18°C)	3 hours	7-8 hours	9-11 hours	8 days
55°F (11°C)	5-6 hours	12-14 hours	16-20 hours	9-10 days
45°F (7°C)	7-8 hours	18-22 hours	28-32 hours	12-13 days
35°F (2°C)	9-11 hours	28-32 hours	46-50 hours	16-18 days

Curing time varies with surface temperature, air movement, humidity and film thickness.

Note: See the Series L69, N69, L140, N140 or V140 product data sheet for cure times for potable water applications.

With: Series 27WB or 1220

Temperature	To Touch	To Handle	To Recoat
75°F (24°C)	1 hour	4 hours	5 hours
55°F (11°C)	1 1/4 hours	5 hours	6 hours
45°F (7°C)	1 1/2 hours	5 hours	7 hours
35°F (2°C)	3 hours	3 days	4 days

Curing time varies with surface temperature, air movement, humidity and film thickness.

VOLATILE ORGANIC COMPOUNDS

0 lbs/gallon (0 grams/litre)

PACKAGING

Individual graduated plastic quarts (0.95 L). Also in multiple 4-quart convenience pack.

NET WEIGHT PER GALLON

8.10 ± 0.10 lbs (3.67 ± .11 kg)

STORAGE TEMPERATURE

Minimum 20°F (-7°C) Maximum 110°F (43°C)

SHELF LIFE

24 months at recommended storage temperature.

FLASH POINT - SETA

None

HEALTH & SAFETY

Paint products contain chemical ingredients which are considered hazardous. Read container label warning and Material Safety Data Sheet for important health and safety information prior to the use of this product.

Keep out of the reach of children.

APPLICATION

MIXING

With: Series L69, N69, L140, N140 or V140

Stir contents of Series L69, N69, L140, N140 or V140 Part A and Part B separately, making sure no pigment remains on the bottom. Accurately add four (4) fluid ounces of 44-700 per gallon of Part A while Part A is under agitation. Continue agitation until thoroughly mixed. Next, add this mixture to Part B while under agitation. Continue agitation until thoroughly mixed. **Note:** Components should be above 50°F (10°C) prior to mixing. For application to surfaces between 35°F to 50°F (2°C to 10°C), allow mixed material to stand thirty (30) minutes and restir before using. For optimum application properties, the material temperature should be above 60°F (16°C). **Note:** The use of more than the recommended ratio of 44-700 will adversely affect coating performance.

With: Series 27WB or 1220

Prior to adding Series 44-700, properly mix the Series 27WB or 1220 components according to the mixing instructions listed on the product data sheet. Accurately add one (1) fluid ounce of 44-700 per mixed gallon of material. Continue agitation until thoroughly mixed. For optimum mixing and application properties, the material temperature should be between 70°F and 85°F (21°C and 29°C). **Note:** The use of more than the recommended ratio of 44-700 will adversely affect coating performance.

POT LIFE

With: Series L69, N69, L140, N140 or V140

2 hours at 50°F (10°C) 1 hour at 75°F (24°C) 30 minutes at 100°F (38°C).

With: Series 27WB or 1220

2 hours at 40°F (4°C) 1 1/2 hours at 60°F (15°C) 45 minutes at 75°F (24°C).

Note: Series 44-700 Accelerator is not recommended for use with Series 27WB or 1220 when temperatures exceed 75°F (24°C).

EPOXY ACCELERATOR | SERIES 44-700

SPRAY LIFE

With: Series L69, N69, L140, N140 or V140
30 minutes at 75°F (24°C)

Note: Spray application after listed times will adversely affect ability to achieve recommended dry film thickness.

SURFACE TEMPERATURE

With: Series 27WB or 1220
1 1/2 hours at 40°F (4°C) 45 minutes at 75°F (24°C)

Minimum 35°F (2°C) Maximum 135°F (57°C)
Cure time necessary to resist direct contact with moisture at surface temperature when used with Series 27WB or 1220

Temperature	To Resist Moisture
75°F (24°C)	5 hours
55°F (13°C)	16 hours
45°F (7°C)	24 hours
35°F (2°C)	4 days

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.