



PRODUCT PROFILE

GENERIC DESCRIPTION Modified Polycarbamide

COMMON USAGE An advanced technology finish coat combining low VOC with exceptional performance. Offers superior color and gloss retention compared to traditional polyurethanes for long-term aesthetics on a wide range of exterior structures. Durable film stands up to exterior weathering. Very good brush, roll and spray application characteristics. Direct-to-Metal capability allows for a labor-saving, high-build, single coat application. NOT FOR IMMERSION SERVICE.

COLORS Refer to Tnemec Color Guide. **Note:** Certain colors may require multiple coats depending on method of application and finish coat color. When feasible, the preceding coat should be in the same color family (blue, gray, etc.), but noticeably different.

FINISH Semi-gloss

COATING SYSTEM

PRIMERS **Steel:** Self-priming or Series 1, 20HS, FC20HS, 27, 27WB, 66, 66HS, L69, L69F, N69, N69F, 73, 90G-1K97, 90-97, H90-97, 91-H₂O, 94-H₂O, 135, L140, L140F, N140, N140F, V140, V140F, 161, 161HS, 394, 1075
Concrete: Series 1, 20HS, FC20HS, 27, 27WB, 66, 66HS, L69, L69F, N69, N69F, 161, 161HS, 1254
Note: Series 20HS, 66, 66HS, L69, N69, 135, L140, N140, or V140 exposed more than 21 days; Series FC20HS, 27, L69F, N69F, L140F, N140F, V140F, 161 or 161HS exposed more than 14 days; and Series 27WB, 73, or 1075 exposed more than 90 days must first be scarified or reprimed with themselves (or with an epoxy for 73 and 1075) prior to topcoating. Brush blasting with fine abrasive is the preferred method of scarification.

TOPCOATS Series 700, V700, 701, V701, 740, 1070, 1070V, 1071, 1071V, 1072, 1072V, 1077, 1078
Note: When topcoating Series 750 with itself, or any of the above listed topcoats, the maximum recoat time is 45 days.

SURFACE PREPARATION

STEEL SSPC-SP6/NACE 3 Commercial Blast Cleaning with a minimum angular anchor profile of 2.0 mils.

ALL SURFACES Must be clean, dry and free of oil, grease and other contaminants when used as a topcoat. See primer product data sheet for surface preparation recommendation.

TECHNICAL DATA

VOLUME SOLIDS 72.0 ± 2.0% (mixed) †

RECOMMENDED DFT **Topcoat Service:** 2.5 to 6.0 mils (65 to 150 microns) per coat.
Direct-to-Metal Service: 6.0 to 8.0 mils (150 to 205 microns).
Note: Number of coats and thickness requirements will vary with substrate, application method and exposure. Contact your Tnemec representative.

CURING TIME

Temperature	To Touch	To Handle	To Recoat	To Resist Moisture
75°F (24°C)	2 hours	6-8 hours	8 hours	13 hours

Curing time varies with surface temperature, air movement, humidity and film thickness. **Note:** For faster time-to-moisture resistance and low-temperature applications, add No. 44-712 Urethane Accelerator; see separate product data sheet.

VOLATILE ORGANIC COMPOUNDS

Unthinned: 0.82 lbs/gallon (99 grams/litre)
Thinned 10% (No. 68 Thinner): 0.82 lbs/gallon (99 grams/litre)
Thinned 10% (No. 49 Thinner): 0.82 lbs/gallon (99 grams/litre) †

HAPS

Unthinned: 0 lbs/gal solids
Thinned 10% (No. 68 Thinner): 0 lbs/gal solids
Thinned 10% (No. 49 Thinner): 0 lbs/gal solids

THEORETICAL COVERAGE

1155 mil sq ft/gal (28.3 m²/L at 25 microns) †

NUMBER OF COMPONENTS

Two: Part A and Part B

MIXING RATIO

By volume: Four (Part A) to one (Part B)

PACKAGING

	PART A (Partially filled)	PART B (Partially filled)	When Mixed
Large Kit	5 gallon pail	1 gallon can	3 gallons (11.3L)
Small Kit	1 gallon pail	1 quart can	1 gallon (3.79L)

NET WEIGHT PER GALLON

12.47 ± 0.25 lbs (5.66 ± .11 kg) †

STORAGE TEMPERATURE

Minimum 20°F (-7°C) Maximum 110°F (43°C)

TEMPERATURE RESISTANCE

(Dry) Continuous 250°F (121°C) Intermittent 275°F (135°C)

SHELF LIFE

12 months at recommended storage temperature.

FLASH POINT - SETA

Part A: 105°F (41°C) Part B: 109°F (43°C)

HEALTH & SAFETY

Paint products contain chemical ingredients which are considered hazardous. Read container label warning and Material Safety Data Sheet for important health and safety information prior to the use of this product.
Keep out of the reach of children.

UVX | SERIES 750

APPLICATION

COVERAGE RATES

Topcoat Service

	Dry Mils (Microns)	Wet Mils (Microns)	Sq Ft/Gal (m ² /Gal)
Suggested	4.0 (100)	5.5 (140)	289 (26.8)
Minimum	2.5 (65)	3.5 (90)	462 (42.9)
Maximum	6.0 (150)	8.0 (205)	195 (18.1)

Direct-to-Metal Service

	Dry Mils (Microns)	Wet Mils (Microns)	Sq Ft/Gal (m ² /Gal)
Minimum	6.0 (150)	8.0 (205)	195 (18.1)
Maximum	8.0 (205)	11.0 (280)	146 (13.6)

Allow for overspray and surface irregularities. Film thickness is rounded to the nearest 0.5 mil or 5 microns. Application of coating below minimum or above maximum recommended dry film thicknesses may adversely affect coating performance. †

MIXING

Stir contents of the container marked Part A, making sure no pigment remains on the bottom. Add the contents of the can marked Part B to Part A while under agitation. Continue agitation until the two components are thoroughly mixed. Do not use mixed material beyond pot life limits. **Caution: Part B is moisture-sensitive and will react with atmospheric moisture. Keep unused material tightly closed at all times.**

THINNING

For air or airless spray, thin up to 10% or 1/2 pint (380 mL) per gallon with No. 68 Thinner. For brush or roller, thin up to 10% or 1/2 pint (380 mL) per gallon with No. 49 Thinner. Thinning is required for proper brush or roller application. **Caution: Do not add thinner if more than thirty (30) minutes have elapsed after mixing.**

POT LIFE

1 hour at 75°F (24°C)

APPLICATION EQUIPMENT

Air Spray

Gun	Fluid Tip	Air Cap	Air Hose ID	Mat'l Hose ID	Atomizing Pressure	Pot Pressure
DeVilbiss JGA	E	765 or 704	5/16" or 3/8" (7.9 or 9.5 mm)	3/8" or 1/2" (9.5 or 12.7 mm)	50-65 psi (3.4-4.5 bar)	10-20 psi (0.7-1.4 bar)

Low temperatures or longer hoses require higher pot pressure.

Airless Spray

Tip Orifice	Atomizing Pressure	Mat'l Hose ID	Manifold Filter
0.015"-0.019" (380-480 microns)	3500-4000 psi (240-275 bar)	1/4" or 3/8" (6.4 or 9.5 mm)	60 mesh (250 microns)

Use appropriate tip/atomizing pressure for equipment, applicator technique and weather conditions.

Roller: Use 1/4" or 3/8" (6.4 mm or 9.5 mm) synthetic woven nap roller cover. Do not use long nap roller covers.

Brush: Use high quality natural or synthetic bristle brushes.

Note: Two or more coats may be required to obtain recommended film thicknesses.

SURFACE TEMPERATURE

Minimum 40°F (4°C) Maximum 120°F (49°C)

The surface should be dry and at least 5°F (3°C) above the dew point. Cure time necessary to resist direct contact with moisture at surface temperature: 75°F (24°C): 13 hours. If the coating is exposed to moisture before the preceding cure parameters are met, dull, flat or spotty-appearing areas may develop. Actual times will vary with air movement, film thickness and humidity.

CLEANUP

Flush and clean all equipment immediately after use with the recommended thinner, xylene or MEK, or use appropriate cleanup solvents that comply with applicable regulations. Use Tnemec No. 74 Thinner when needed to comply with VOC regulations.

† Values may vary with color.

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.