



PRODUCT PROFILE

GENERIC DESCRIPTION Polyamide Epoxy

COMMON USAGE A high-solids, lower VOC version of Tnemec's proven polyamide epoxy technology for steel and concrete substrates. Fast-cure properties are ideal for shop and low temperature application. Certified for use on potable water tanks, pipes, and valves.

COLORS 1211 Red, 1255 Beige, 00WH Tnemec White, 15BL Tank White, 35GR Black, 39BL Delft Blue. **Note:** Epoxies chalk with extended exposure to sunlight and may yellow on aging. Lack of ventilation, incomplete mixing, miscatalyzation or the use of heaters that emit carbon dioxide and carbon monoxide during application and initial stages of curing may accelerate any potential yellowing.

FINISH Satin

SPECIAL QUALIFICATIONS Certified by **NSF International** in accordance with **NSF/ANSI Std. 61**. Seven day ambient air cured Series FC20HS is qualified for interior use on tanks and reservoirs of 300 gallons (1,135 L) capacity or greater, pipes 18 inches (46 cm) in diameter or greater, valves 3.5 inches (9 cm) in diameter or greater, fittings 1 inch (3 cm) in diameter or greater and pumps 3.5 inches (9 cm) or greater. Sixty day ambient air cured Series FC20HS is qualified for use on pipes 14 inches (35 cm) in diameter or greater. Reference the "Search Listings" section of the NSF website at www.nsf.org for details on the maximum allowable DFT. Conforms to **AWWA D102 Inside Systems No. 1 and No. 2**. Conforms to **AWWA C210**. Contact your Tnemec representative for systems and additional information.

COATING SYSTEM

SURFACER/FILLER/PATCHER 215, 217, 218

PRIMERS **Steel:** Self-priming or Series 1, 20, FC20, 20HS, 91-H₂O, 94-H₂O, L140, L140F, N140, N140F, V140, V140F
Concrete: Self-priming, 20, 20HS

TOPCOATS **Interior:** FC20, FC20HS, 22, FC22, L140, L140F, N140, N140F, V140, V140F, 264, 265, 406
Exterior: FC20, FC20HS, L69, L69F, N69, N69F, 72, 73, 113, 114, L140, L140F, N140, N140F, V140, V140F, 264, 265, 406, 700, V700, 701, V701, 740, 750, 1074, 1074U, 1075, 1075U, 1095.
Refer to COLORS on applicable topcoat data sheets for additional information. **Note:** When topcoating Series FC20HS, the following recoat times apply: with 264 or 265, 7 days; with Series 406, 740 or 750, 14 days; with 1095, 30 days; with itself, FC20, L69, L69F, N69, N69F, 113, 114, L140, L140F, N140, N140F, V140, V140F, 700, V700, 701 and V701, 60 days; with 72, 73, 1074, 1074U, 1075 and 1075U, 90 days. Scarify the Series FC20HS surface before topcoating if maximum recoat time has elapsed.

SURFACE PREPARATION

PRIMED STEEL **Immersion Service:** Scarify the epoxy prime coat surface by abrasive-blasting with a fine abrasive before topcoating if more than 60 days has elapsed since initial application.

STEEL **Immersion Service:** SSPC-SP10/NACE 2 Near-White Blast Cleaning or ISO Sa 2 1/2 Very Thorough Blast Cleaning with a minimum angular anchor profile of 1.5 mils.
Non-Immersion Service: SSPC-SP6/NACE 3 Commercial Blast Cleaning or ISO Sa 2 Thorough Blast Cleaning with a minimum angular anchor profile of 1.5 mils.

CAST/DUCTILE IRON Contact your Tnemec representative or Tnemec Technical Services.

CONCRETE Allow new concrete to cure 28 days. For optimum results and/or immersion service, abrasive blast referencing SSPC-SP13/NACE 6 Surface Preparation of Concrete and Tnemec's Surface Preparation and Application Guide.

PAINTED SURFACES **Non-Immersion Service:** Ask your Tnemec representative for specific recommendations.

ALL SURFACES Must be clean, dry and free of oil, grease and other contaminants.

TECHNICAL DATA

VOLUME SOLIDS 78% ± 2.0% (mixed)†

RECOMMENDED DFT 2.0 to 10.0 mils (50 to 254 microns) per coat.
Note: Number of coats and thickness requirements will vary with substrate, application method and exposure. Contact your Tnemec representative.

CURING TIME

Temperature	To Touch	To Handle	To Recoat	Immersion†
75°F (24°C)	1 hour	6 hours	7-8 hours	5 days
65°F (18°C)	2 hours	6-8 hours	8-10 hours	7 days
55°F (13°C)	3 hours	10-12 hours	14-16 hours	9 days
45°F (7°C)	5 hours	18-20 hours	22-24 hours	10 days
35°F (2°C)	6 hours	30 hours	36-40 hours	16 days

† For water immersion only. Chemical storage will require additional cure time. Curing time varies with surface temperature, air movement, humidity and film thickness.
Ventilation: When used as a tank lining or in enclosed areas, provide adequate ventilation during application and cure.

VOLATILE ORGANIC COMPOUNDS **Unthinned:** 1.53 lbs/gal (184 grams/litre)
Thinned 10% (No. 4 Thinner): 2.02 lbs/gal (242 grams/litre) †

HAPS **Unthinned:** 1.15 lbs/gal solids
Thinned 10% (No. 4 Thinner): 1.87 lbs/gal solids

THEORETICAL COVERAGE 1,248 mil sq ft/gal (30.7 m²/L at 25 microns). See APPLICATION for coverage rates. †

POTA-POX® | SERIES FC20HS

NUMBER OF COMPONENTS	Two: Part A (epoxy) and Part B (polyamide)												
MIXING RATIO	One (Part A) to one (Part B) by volume.												
PACKAGING	<table border="1"> <thead> <tr> <th></th> <th>Part A</th> <th>Part B</th> <th>When Mixed Yield</th> </tr> </thead> <tbody> <tr> <td>Large Kit</td> <td>5 gallon pail</td> <td>5 gallon pail</td> <td>10 gallons (37.9 L)</td> </tr> <tr> <td>Small Kit</td> <td>1 gallon can</td> <td>1 gallon can</td> <td>2 gallons (7.57 L)</td> </tr> </tbody> </table>		Part A	Part B	When Mixed Yield	Large Kit	5 gallon pail	5 gallon pail	10 gallons (37.9 L)	Small Kit	1 gallon can	1 gallon can	2 gallons (7.57 L)
	Part A	Part B	When Mixed Yield										
Large Kit	5 gallon pail	5 gallon pail	10 gallons (37.9 L)										
Small Kit	1 gallon can	1 gallon can	2 gallons (7.57 L)										
NET WEIGHT PER GALLON	13.03 lbs ± 0.25 lbs (5.91 ± .11 kg) (mixed) †												
STORAGE TEMPERATURE	Minimum 20°F (-7°C) Maximum 110°F (43°C)												
TEMPERATURE RESISTANCE	(Dry) Continuous 250°F (121°C) Intermittent 275°F (135°C)												
SHELF LIFE	Part A: 24 months; Part B: 24 months at recommended storage temperature.												
FLASH POINT - SETA	Part A: 80°F (27°C) Part B: 105°F (41°C)												
HEALTH & SAFETY	Paint products contain chemical ingredients which are considered hazardous. Read container label warning and Safety Data Sheet for important health and safety information prior to the use of this product. Keep out of the reach of children.												

APPLICATION

COVERAGE RATES	Dry MILS (MICRONS)	Wet MILS (MICRONS)	Sq Ft/Gal (m ² /Gal)
Suggested	5.0 (125)	6.5 (163)	250 (23.2)
Minimum	2.0 (50)	2.5 (63)	625 (58)
Maximum	10.0 (254)	13.0 (330)	125 (11.6)

Note: Roller or brush application requires two or more coats to obtain recommended film thickness. Allow for overspray and surface irregularities. Wet film thickness is rounded to the nearest 0.5 mil or 5 microns. Application of coating below minimum or above maximum recommended dry film thicknesses may adversely affect coating performance. †

MIXING Power mix contents of each container, making sure no pigment remains on the bottom. Pour a measured amount of Part B into a clean container large enough to hold both components. Add an equal volume of Part A to Part B while under agitation. Continue agitation until the two components are thoroughly mixed. Do not use mixed material beyond pot life limits. **Note:** For applications between 35°F to 50°F (2°C to 10°C), allow mixed material to stand thirty (30) minutes and restir before using. To avoid this induction time, both components should be above 50°F (10°C) prior to mixing. Mixing ratio is one to one by volume.

THINNING For air, airless spray, roller or brush applications thin up to 10% or 12.8 ounces (380 mL) per gallon with No. 4 Thinner. **Caution: Series FC20HS NSF/ANSI Std. 61 certification is based on thinning with No. 4 Thinner.** Use of any other thinner voids NSF/ANSI Std. 61 certification.

POT LIFE & SPRAY LIFE

10% Thinning:

Temperature	Pot Life	Spray Life
75°F (24°C)	1.5 hours	75 minutes
55°F (13°C)	2 hours	1.5 hours

APPLICATION EQUIPMENT

Air Spray

Gun	Fluid Tip	Air Cap	Air Hose ID	Mat'l Hose ID	Atomizing Pressure	Pot Pressure
DeVilbiss JGA	E	765 or 704	5/16" or 3/8" (7.9 or 9.5 mm)	3/8" or 1/2" (9.5 or 12.7 mm)	50-80 psi (3.4-5.5 bar)	20-25 psi (1.4-1.7 bar)

Low temperatures or longer hoses require higher pot pressure.

Airless Spray

Tip Orifice	Atomizing Pressure	Mat'l Hose ID	Manifold Filter
0.015"-0.021" (380-530 microns)	3000-4500 psi (207-310 bar)	3/8" or 1/2" (9.5 or 12.7 mm)	60 mesh (250 microns)

Use appropriate tip/atomizing pressure for equipment, applicator technique and weather conditions.

Note: A minimum pump size of 45:1 is required for proper airless spray application.

Roller: Use 3/8" or 1/2" (9.5 mm to 12.7 mm) high quality synthetic woven nap covers.

Brush: Recommended for small areas only. Use high quality natural or synthetic bristle brushes.

SURFACE TEMPERATURE Minimum 35°F (2°C) Maximum 135°F (57°C)
The surface should be dry and at least 5°F (3°C) above the dew point. Coating will not cure below minimum surface temperature.

CLEANUP Flush and clean all equipment immediately after use with No. 4 thinner or MEK.
† Values may vary with color.

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.