



## POTA-POX® PLUS SERIES L140F

## PRODUCT PROFILE

<b>GENERIC DESCRIPTION</b>	Polyamidoamine Epoxy
<b>COMMON USAGE</b>	Versatile epoxy coating (factory accelerated version of L140) for protection and finishing of steel. It has excellent resistance to abrasion and is suitable for immersion service. This product can be used for lining storage tanks that contain demineralized, deionized or distilled water.
<b>COLORS</b>	1255 Beige, 1211 Red, 15BL Tank White. <b>Note:</b> Epoxies chalk with extended exposure to sunlight. Lack of ventilation, incomplete mixing, miscatalyzation or the use of heaters that emit carbon dioxide and carbon monoxide during application and initial stages of curing may cause yellowing to occur.
<b>SPECIAL QUALIFICATIONS</b>	Certified by <b>NSF International</b> in accordance with <b>ANSI/NSF Std. 61</b> . Series L140F is qualified for use on tanks of 50,000 gallons (189,270.6L) capacity or greater and fittings one (1) inch (2.5 cm) in diameter or greater. Reference Tnemec's certified product listing at <a href="http://www.nsf.org">www.nsf.org</a> for more details on maximum allowable DFT.

## COATING SYSTEM

<b>SURFACER/FILLER/PATCHER</b>	Series 215, 217, 218
<b>PRIMERS</b>	Self-priming, or Series 1, 91-H <sub>2</sub> O, 94-H <sub>2</sub> O, N140, N140F, L140, V140, V140F, 141
<b>TOPCOATS</b>	<b>Interior:</b> Series 22, FC22, L140, L140F, N140, N140F, V140, V140F, 141 <b>Exterior:</b> Series 22, 27, 27WB, 30, 66, L69, L69F, N69, N69F, V69, V69F, 72, 73, 118, L140, L140F, N140, N140F, V140, V140F, 141, 156, 157, 161, 180, 181, 446, 700, V700, 701, V701, 740, 750, 1026, 1028, 1029, 1074, 1074U, 1075, 1075U, 1078, 1078V, 1080, 1081, 1094, 1095, 1096, 1224. <b>Note:</b> When topcoating with Series 700, V700, 701, or V701, an intermediate coat of Series 73, 1075, 1075U, 1095 or 1096 is required. <b>Note:</b> The following recoat times apply for Series L140F: Immersion Service—Surface must be scarified after 30 days. Atmospheric Service—After 30 days, scarification or an epoxy tie-coat is required. When topcoating with Series 740 or 750, recoat time for L140F is 14 days. Contact your Tnemec representative for specific recommendations.

## SURFACE PREPARATION

<b>STEEL</b>	<b>Immersion Service:</b> SSPC-SP10/NACE 2 Near-White Blast Cleaning or ISO Sa 2 1/2 Very Thorough Blast Cleaning with a minimum angular anchor profile of 1.5 mils. <b>Non-Immersion Service:</b> SSPC-SP6/NACE 3 Commercial Blast Cleaning or ISO Sa 2 Thorough Blast Cleaning with a minimum angular anchor profile of 1.5 mils. <b>Note:</b> Commercial Blast Cleaning generally produces the best coating performance for this exposure. If conditions will not permit this, in moderate exposures Series L140F may be applied to SSPC-SP2 or SP3 Hand or Power Tool Cleaned surfaces (SSPC Rust Grade Condition C).
<b>CAST/DUCTILE IRON</b>	All external surfaces of ductile iron pipe and fittings shall be delivered to the application facility without asphalt or any other protective lining on the exterior surface. All oils, small deposits of asphalt paint, grease, and soluble deposits should be removed and uniformly abrasive blasted using angular abrasive in accordance with NAPF 500-03-04: External Pipe Surface condition. When viewed without magnification, the exterior surfaces shall be free of all visible dirt, dust, loose annealing oxide, rust, mold coating and other foreign matter. Any area where rust reappears before application shall be reblasted. The surface shall contain a minimum angular anchor profile of 1.5 mils (38.1 microns) (Reference NACE RP0287 or ASTM D 4417, Method C).
<b>CONCRETE</b>	Allow new cast-in-place concrete to cure a minimum of 28 days at 75°F (24°C). Verify concrete dryness in accordance with ASTM F 1869 "Standard Test Method for Measuring Moisture Vapor Emission Rate of Concrete Subfloor Using Anhydrous Calcium Chloride" (moisture vapor transmission should not exceed three pounds per 1,000 square feet in a 24 hour period), F 2170 "Standard Test Method for Determining Relative Humidity in Concrete using in situ Probes" (relative humidity should not exceed 80%), or D 4263 "Standard Test Method for Indicating Moisture in Concrete by the Plastic Sheet Method" (no moisture present). Prepare concrete surfaces in accordance with NACE No. 6/SSPC-SP13 Joint Surface Preparation Standards and ICRI Technical Guidelines. Abrasive blast, shot-blast, water jet or mechanically abrade concrete surfaces to remove laitance, curing compounds, hardeners, sealers and other contaminants and to provide an ICRI-CSP 2-3 surface profile. Large cracks, voids and other surface imperfections should be filled with a recommended filler or surfacer.
<b>PAINTED SURFACES</b>	<b>Non-Immersion Service:</b> Ask your Tnemec representative for specific recommendations.
<b>PRIMED SURFACES</b>	<b>Immersion Service:</b> Scarify the Series L140F prime coat surface by abrasive-blasting with a fine abrasive before topcoating if the Series L140F prime coat has been in exterior exposure for 30 days or longer and Series 66, L69, L69F, N69, N69F, V69, N69 or 161 is the specified topcoat.
<b>ALL SURFACES</b>	Must be clean, dry and free of oil, grease and other contaminants.

## TECHNICAL DATA

<b>VOLUME SOLIDS</b>	66.0 ± 2.0% (mixed) †
<b>RECOMMENDED DFT</b>	2.0 to 10.0 mils (50 to 255 microns) per coat. <b>Note:</b> Dry film thickness that exceeds published recommendations but is in compliance with SSPC PA-2 and ANSI/NSF Std. 61 certifications, is acceptable. <b>Note:</b> Number of coats and thickness requirements will vary with substrate, application method and exposure. Contact your Tnemec representative.

# POTA-POX<sup>®</sup> PLUS | SERIES L140F

**CURING TIME AT 5 MILS DFT**

Temperature	To Handle	To Recoat	Immersion
75°F (24°C)	4 hours	5 hours	7 days
65°F (18°C)	7-8 hours	9-11 hours	8 days
55°F (13°C)	12-14 hours	16-20 hours	9-10 days
45°F (7°C)	18-22 hours	28-32 hours	12-13 days
35°F (2°C)	28-32 hours	46-50 hours	16-18 days

Curing time varies with surface temperature, air movement, humidity and film thickness. **Ventilation:** When used in enclosed areas, provide adequate ventilation during application and cure. **Note:** Refer to product listings on [www.nsf.org](http://www.nsf.org) for specific potable water return to service information.

**VOLATILE ORGANIC COMPOUNDS**

**Unthinned:** 0.79 lbs/gallon (95 grams/litre)  
**Thinned 5% (No. 49 Thinner):** 0.79 lbs/gallon (95 grams/litre) †

**HAPS**

**Unthinned:** 0 lbs/gal solids  
**Thinned 5% (No. 49 Thinner):** 0 lbs/gal solids

**THEORETICAL COVERAGE**

1,059 mil sq ft/gal (26.0 m<sup>2</sup>/L at 25 microns). See APPLICATION for coverage rates. †

**NUMBER OF COMPONENTS**

Two: Part A (amine) and Part B (epoxy) — One (Part A) to one (Part B) by volume.

**PACKAGING**

	Part A	Part B	Yield (mixed)
Large Kit	5 gallon pail	5 gallon pail	10 gallons (37.9 L)
Small Kit	1 gallon can	1 gallon can	2 gallons (7.6 L)

**NET WEIGHT PER GALLON**

14.62 ± 0.25 lbs (6.63 ± .11 kg) (mixed) †

**STORAGE TEMPERATURE**

Minimum 20°F (-7°C) Maximum 110°F (43°C)  
 For optimum application properties, material temperature should be above 60°F (16°C) prior to application.

**TEMPERATURE RESISTANCE**

(Dry) Continuous 250°F (121°C) Intermittent 275°F (135°C)

**SHELF LIFE**

Part A: 24 months; Part B: 12 months at recommended storage temperature.

**FLASH POINT - SETA**

Part A: 98°F (37°C) Part B: 95°F (35°C)

**HEALTH & SAFETY**

Paint products contain chemical ingredients which are considered hazardous. Read container label warning and Material Safety Data Sheet for important health and safety information prior to the use of this product.  
**Keep out of the reach of children.**

**APPLICATION**

**COVERAGE RATES**

	Dry MILS (Microns)	Wet MILS (Microns)	Sq Ft/Gal (m <sup>2</sup> /Gal)
Suggested	6.0 (150)	9.0 (230)	176 (16.4)
Minimum	2.0 (50)	3.0 (75)	529 (49.2)
Maximum	10.0 (255)	15.0 (375)	106 (9.8)

**Note:** Roller or brush application requires two or more coats to obtain recommended film thickness. Allow for overspray and surface irregularities. Wet film thickness is rounded to the nearest 0.5 mil or 5 microns. Application of coating below minimum or above maximum recommended dry film thicknesses may adversely affect coating performance. Reference the NSF website at [www.nsf.org](http://www.nsf.org) for details on the maximum allowable DFT. †

**MIXING**

Start with equal amounts of Series L140F Parts A and B. Power mix contents of each container separately, making sure no pigment remains on the bottom. Pour a measured amount of Part B into a clean container large enough to hold both components. Add an equal volume of Part A to Part B while under agitation. Continue agitation until the two components are thoroughly mixed. **Note:** Both components must be above 50°F (10°C) prior to mixing. For optimum mixing and application properties, the material should be above 60°F (16°C).

Thin by volume and thoroughly mix. Failure to thoroughly mix the Part A and Part B components prior to thinning can affect product's gloss and performance. Do not use mixed material beyond pot life limits. **Note:** For application to surfaces between 35°F to 50°F (2°C to 10°C), allow mixed material to stand 30 minutes and restir before using.

**THINNING**

Use No. 49 Thinner. For air spray, thin up to 5% or 1/4 pint (190 mL) per gallon. No thinning necessary for airless spray. For roller or brush application, thin up to 5% or 1/4 pint (190 mL) per gallon. **Caution: Series L140F NSF certification is based on thinning with No. 49 Thinner only. Use of any other thinner voids ANSI/NSF Std 61.**

**POT LIFE**

2 hours at 50°F (10°C) 1 hour at 75°F (24°C) 30 minutes at 100°F (38°C)

**SPRAY LIFE**

30 minutes at 75°F (24°C)  
**Note:** Spray application after listed times will adversely affect ability to achieve recommended dry film thickness.

# POTA-POX® PLUS | SERIES L140F

**APPLICATION EQUIPMENT**

**Air Spray**

Gun	Fluid Tip	Air Cap	Air Hose ID	Mat'l Hose ID	Atomizing Pressure	Pot Pressure
DeVilbiss JGA	E	704	5/16" or 3/8" (7.9 or 9.5 mm)	3/8" or 1/2" (9.5 or 12.7 mm)	50-80 psi (3.4-5.5 bar)	10-20 psi (0.7-1.4 bar)

Low temperatures or longer hoses require higher pot pressure.

**Airless Spray**

Tip Orifice	Atomizing Pressure	Mat'l Hose ID	Manifold Filter
0.015"-0.019" (380-485 microns)	3500-5100 psi (241-351 bar)	1/4" or 3/8" (6.4 or 9.5 mm)	60 mesh (250 microns)

Use appropriate tip/atomizing pressure for equipment, applicator technique and weather conditions.

**Roller:** Use a 3/8" or 1/2" (9.5 mm or 12.7 mm) synthetic woven nap roller cover. Use longer nap to obtain penetration on rough or porous surfaces.

**Brush:** Recommended for small areas only. Use high quality natural or synthetic bristle brushes.

**SURFACE TEMPERATURE**

Minimum 35°F (2°C) Maximum 135°F (57°C)

The surface should be dry and at least 5°F (3°C) above the dew point. Coating will not cure below minimum surface temperature.

**CLEANUP**

Flush and clean all equipment immediately after use with the recommended thinner or MEK.

† Values may vary with color.

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.