



POTA-POX® PLUS SERIES V140

PRODUCT PROFILE

GENERIC DESCRIPTION	Polyamidoamine Epoxy
COMMON USAGE	Innovative potable water coating which offers high-build edge protection and allows for application at a wide range of temperatures (down to 35°F or 2°C with 44-700 Accelerator). For use on the interior and exterior of steel or concrete tanks, reservoirs, pipes, valves, pumps and equipment in potable water service.
COLORS	1211 Red, 1255 Beige, 00WH Tnemec White, 15BL Tank White. Note: Epoxies chalk with extended exposure to sunlight. Lack of ventilation, incomplete mixing, miscatalyzation or the use of heaters that emit carbon dioxide and carbon monoxide during application and initial stages of curing may cause yellowing to occur.
SPECIAL QUALIFICATIONS	Certified by NSF International in accordance with ANSI/NSF Std. 61 . Series V140 is qualified for use on tanks of 50,000 gallons (189,270L) capacity or greater, valves 2 1/2 inches (6 cm) in diameter or greater and fittings 3/4 inch (2 cm) in diameter or greater. Reference Tnemec's certified product listing at www.nsf.org for details on maximum allowable DFT. Conforms to AWWA D 102 Inside Systems No. 1 and No. 2 (with or without 44-700). Conforms to AWWA C 210 (without 44-700). Contact your Tnemec representative for systems and additional information.

COATING SYSTEM

SURFACER/FILLER/PATCHER	Series 215, 217, 218
PRIMERS	Self-priming or Series 22, 91-H ₂ O, 94-H ₂ O, L140, L140F, N140, N140F, V140F, 141
TOPCOATS	Interior: Series 22, FC22, 264, 265, L140, L140F, N140, N140F, V140, V140F, 141, 406. Exterior: Series 22, 27, 27WB, 30, 66, L69, L69F, N69, N69F, V69, V69F, 72, 73, 118, L140, L140F, N140, N140F, V140, V140F, 141, 156, 157, 161, 180, 181, 446, 700, V700, 701, V701, 740, 750, 1026, 1028, 1029, 1074, 1074U, 1075, 1075U, 1077, 1078, 1078V, 1080, 1081, 1094, 1095, 1096, 1224. Note: When topcoating with Series 700, V700, 701 or V701, an intermediate coat of Series 73, 1075, 1075U, 1095 or 1096 is required. Note: The following recoat times apply for Series V140: Immersion Service—Surface must be scarified by blasting with fine abrasive after 60 days. Atmospheric Service—After 60 days, scarification or an epoxy tie-coat is required. When topcoating with Series 740 or 750, recoat time for V140 is 21 days. Note: When topcoating with Series 406, recoat times will vary with temperature. Reference the Series 406 product data sheet for specific recoat times. Contact your Tnemec representative for specific recommendations.

SURFACE PREPARATION

STEEL	Immersion Service: SSPC-SP10/NACE 2 Near-White Blast Cleaning or ISO Sa 2 1/2 Very Thorough Blast Cleaning with a minimum angular anchor profile of 1.5 mils. Non-Immersion Service: SSPC-SP6/NACE 3 Commercial Blast Cleaning or ISO Sa 2 Thorough Blast Cleaning with a minimum angular anchor profile of 1.5 mils. Note: Commercial Blast Cleaning generally produces the best coating performance for this exposure. If conditions will not permit this, in moderate exposures Series V140 may be applied to SSPC-SP2 or SP3 Hand or Power Tool Cleaned surfaces (SSPC Rust Grade Condition C).
CAST/DUCTILE IRON	All external surfaces of ductile iron pipe and fittings shall be delivered to the application facility without asphalt or any other protective lining on the exterior surface. All oils, small deposits of asphalt paint, grease, and soluble deposits should be removed and uniformly abrasive blasted using angular abrasive in accordance with NAF 500-03-04: External Pipe Surface condition. When viewed without magnification, the exterior surfaces shall be free of all visible dirt, dust, loose annealing oxide, rust, mold coating and other foreign matter. Any area where rust reappears before application shall be reblasted. The surface shall contain a minimum angular anchor profile of 1.5 mils (38.1 microns) (Reference NACE RP0287 or ASTM D 4417, Method C).
CONCRETE	Allow new cast-in-place concrete to cure a minimum of 28 days at 75°F (24°C). Verify concrete dryness in accordance with ASTM F 1869 "Standard Test Method for Measuring Moisture Vapor Emission Rate of Concrete Subfloor Using Anhydrous Calcium Chloride" (moisture vapor transmission should not exceed three pounds per 1,000 square feet in a 24 hour period), F 2170 "Standard Test Method for Determining Relative Humidity in Concrete using in situ Probes" (relative humidity should not exceed 80%), or D 4263 "Standard Test Method for Indicating Moisture in Concrete by the Plastic Sheet Method" (no moisture present). Prepare concrete surfaces in accordance with NACE No. 6/SSPC-SP13 Joint Surface Preparation Standards and ICRI Technical Guidelines. Abrasive blast, shot-blast, water jet or mechanically abrade concrete surfaces to remove laitance, curing compounds, hardeners, sealers and other contaminants and to provide an ICRI-CSP 2-3 surface profile. Large cracks, voids and other surface imperfections should be filled with a recommended filler or surfacer.
PAINTED SURFACES	Non-Immersion Service: Ask your Tnemec representative for specific recommendations.
PRIMED SURFACES	Immersion Service: Scarify the Series V140 prime coat surface by abrasive-blasting with a fine abrasive before topcoating if: (a) the Series V140 prime coat has been in exterior exposure for 60 days or longer and Series 66, L69, L69F, N69, N69F, V69, V69F, L140, L140F, N140, N140F, V140, V140F or 161 is the specified topcoat; (b) the Series V140 prime coat has been in exterior exposure for 7 days or longer and Series 264 or 265 is the specified topcoat.
ALL SURFACES	Must be clean, dry and free of oil, grease and other contaminants.

TECHNICAL DATA

VOLUME SOLIDS	67.0 ± 2.0% (mixed—A, B & 44-700 Epoxy Accelerator) †
RECOMMENDED DFT	2.0 to 10.0 mils (50 to 225 microns) per coat. Note: Dry film thickness that exceeds published recommendations but is in compliance with SSPC PA-2 and ANSI/NSF Std. 61 certifications, is acceptable. Note: The number of coats and thickness requirements will vary with substrate, application method and exposure. Contact your Tnemec representative.

POTA-POX® PLUS | SERIES V140

CURING TIME AT 5 MILS DFT

Without 44-700 Accelerator:

Temperature	To Handle	To Recoat	Immersion
90°F (32°C)	5 hours	7 hours	7 days
80°F (27°C)	7 hours	9 hours	7 days
70°F (21°C)	9 hours	12 hours	7 days
60°F (16°C)	16 hours	22 hours	9 to 12 days
50°F (10°C)	24 hours	32 hours	12 to 14 days

Curing time varies with surface temperature, air movement, humidity and film thickness. **Note:** For valve applications allow 14 days cure at 75°F (24°C) prior to immersion. For pipe applications allow 30 days cure at 75°F (24°C) prior to immersion. **Ventilation:** When used in enclosed areas, provide adequate ventilation during application and cure. **Note:** Refer to product listing on www.nsf.org for specific potable water return to service information. **Note:** For faster curing and low temperature applications, add No. 44-700 Epoxy Accelerator, see separate product data sheet for cure information.

VOLATILE ORGANIC COMPOUNDS

Unthinned: 1.95 lbs/gallon (234 grams/litre)
Thinned 2.5% (#4): 2.08 lbs/gallon (250 grams/litre) †

HAPS

Unthinned: 2.1 lbs/gal solids
Thinned 2.5% (#4): 2.3 lbs/gal solids

THEORETICAL COVERAGE

1,070 mil sq ft/gal (27.2 m²/L at 25 microns). See APPLICATION for coverage rates. †

NUMBER OF COMPONENTS

Two: Part A (amine) and Part B (epoxy) — One (Part A) to one (Part B) by volume.

PACKAGING

	Part A	Part B	Yield (mixed)
Large Kit	5 gallon pail	5 gallon pail	10 gallons (37.9 L)
Small Kit	1 gallon can	1 gallon can	2 gallons (7.6 L)

Reference 44-700 Epoxy Accelerator product data sheet for its packaging information.

NET WEIGHT PER GALLON

13.00 ± 0.25 lbs (5.90 ± .11 kg) (mixed) †

STORAGE TEMPERATURE

Minimum 20°F (-7°C) Maximum 110°F (43°C)

TEMPERATURE RESISTANCE

(Dry) Continuous 250°F (121°C) Intermittent 275°F (135°C)

SHELF LIFE

Part A: 24 months; Part B: 12 months at recommended storage temperature.

FLASH POINT - SETA

Part A: 82°F (28°C) Part B: 86°F (30°C) 44-700: None

HEALTH & SAFETY

Paint products contain chemical ingredients which are considered hazardous. Read container label warning and Material Safety Data Sheet for important health and safety information prior to the use of this product.
Keep out of reach of children.

APPLICATION

COVERAGE RATES

	Dry MILS (Microns)	Wet MILS (Microns)	Sq Ft/Gal (m ² /Gal)
Suggested	6.0 (150)	9.0 (230)	179 (16.6)
Minimum	2.0 (50)	3.0 (75)	537 (49.9)
Maximum	10.0 (225)	15.0 (375)	107 (10.0)

Note: Roller or brush application requires two or more coats to obtain recommended film thickness. Allow for overspray and surface irregularities. Wet film thickness is rounded to the nearest 0.5 mil or 5 microns. Application of coating below minimum or above maximum recommended dry film thicknesses may adversely affect coating performance. Reference the "Search Listings" section of the NSF website at www.nsf.org for details on the maximum allowable DFT. †

MIXING

Start with equal amounts of Series V140 Parts A and B. Power mix contents of each container separately, making sure no pigment remains on the bottom. Pour a measured amount of Part B into a clean container large enough to hold both components. If Series 44-700 is not being used, proceed with mixing and add an equal volume of Part A to Part B while under agitation. Continue agitation until the two components are thoroughly mixed. **Note:** Both components must be above 50°F (10°C) prior to mixing. For optimum mixing and application properties, the material should be above 60°F (16°C).

If using Series 44-700 accelerator, slowly add four (4) fluid ounces of 44-700 per gallon to Series V140 Part A material while under agitation and proceed with adding Part B. **Note:** The use of more than the recommended amount of 44-700 will adversely affect performance.

Thin by volume and thoroughly mix. Failure to thoroughly mix the Part A and Part B components prior to thinning can affect product's gloss and performance. Do not use mixed material beyond pot life limits. **Note:** For application of the unaccelerated version to surfaces between 50°F to 60°F (10°C to 16°C) or the accelerated version to surfaces between 35°F to 50°F (2°C to 10°C), allow mixed material to stand 30 minutes and restir before using.

Note: The use of more than the recommended amount of 44-700 will adversely affect performance.

THINNING

Use No. 4 Thinner. **Caution: Series V140 NSF certification is based on thinning with No. 4 Thinner only.** Use of any other thinner voids ANSI/NSF Std. 61 certification. **Note:** When using Series V140, a maximum of 2.5% of No. 4 Thinner may be used to comply with VOC regulations.

POT LIFE

Without 44-700 6 hours at 50°F (10°C) 4 hours at 75°F (24°C) 1 hour at 100°F (38°C)
 With 44-700 2 hours at 50°F (10°C) 1 hour at 75°F (24°C) 30 minutes at 100°F (38°C)

SPRAY LIFE

Without 44-700: 1 hour at 77°F (25°C) With 44-700: 30 minutes at 75°F (24°C)

Note: Spray application after listed times will adversely affect ability to achieve recommended dry film thickness.

POTA-POX® PLUS | SERIES V140

APPLICATION EQUIPMENT

Air Spray

Gun	Fluid Tip	Air Cap	Air Hose ID	Mat'l Hose ID	Atomizing Pressure	Pot Pressure
DeVilbiss JGA	E	765 or 704	5/16" or 3/8" (7.9 or 9.5 mm)	3/8" or 1/2" (9.5 or 12.7 mm)	50-80 psi (3.4-5.5 bar)	10-20 psi (0.7-1.4 bar)

Airless Spray

Tip Orifice	Atomizing Pressure	Mat'l Hose ID	Manifold Filter
0.015"-0.019" (380-485 microns)	3000-4800 psi (207-330 bar)	1/4" or 3/8" (6.4 or 9.5 mm)	60 mesh (250 microns)

Low temperatures or longer hoses require higher pot pressure. Use appropriate tip/atomizing pressure for equipment, applicator technique and weather conditions.

Roller: Use 3/8" or 1/2" (9.5 mm to 12.7 mm) synthetic woven nap roller cover. Use longer nap to obtain penetration on rough or porous surfaces.

Brush: Recommended for small areas only. Use high quality natural or synthetic bristle brushes.

SURFACE TEMPERATURE

Without 44-700: Min. 50°F (10°C), Max. 135°F (57°C) With 44-700: Min. 35°F (2°C), Max. 135°F (57°C)

The surface should be dry and at least 5°F (3°C) above the dew point. Coating will not cure below minimum surface temperature.

CLEANUP

Flush and clean all equipment immediately after use with the recommended thinner or MEK.

† Values may vary with color.

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.